

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 June 2001 (07.06.2001)

PCT

(10) International Publication Number
WO 01/40374 A2

(51) International Patent Classification⁷: **C08L 51/00**

DELLAMEA, Jennifer [US/US]; 420 Garland Drive,
Lake Jackson, TX 77566 (US).

(21) International Application Number: PCT/US00/32748

(22) International Filing Date: 1 December 2000 (01.12.2000)

(74) Agent: **SPENCER, Lee**; Intellectual Property, B-1211,
2301 Brazosport Blvd., Freeport, TX 77541 (US).

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/168,702 3 December 1999 (03.12.1999) US

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, YU, ZA, ZW.

(63) Related by continuation (CON) or continuation-in-part (CIP) to earlier application:
US 60/168,702 (CIP)
Filed on 3 December 1999 (03.12.1999)

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **THE DOW CHEMICAL COMPANY** [US/US]; 2030 Dow Center, Midland, MI 48674 (US).

Published:

— Without international search report and to be republished upon receipt of that report.

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **CHAUDHARY, Bharat, I.** [IN/US]; 3419 Woodbine Place, Pearland, TX 77584 (US). **HO, Thoi, H.** [US/US]; 54 Orchid Court, Lake Jackson, TX 77566 (US). **OSWALD, Thomas, T.** [US/US]; 323 Huckleberry, Lake Jackson, TX 77566 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: GRAFTED THERMOPLASTIC COMPOSITIONS AND FABRICATED ARTICLES THEREFROM

(57) Abstract: This invention describes grafted blend compositions, processes for their preparation and fabricated articles, especially foams therefrom. The blends exhibit enhanced melt strength, melt elongation greater than or equal to about 20 mm/s, increased upper service temperature, increased modulus, and increased hardness. The grafted blend compositions have little or no high shear viscosity increase over a corresponding polymer of the same chemical composition absent the coupling agent.

WO 01/40374 A2

GRAFTED THERMOPLASTIC COMPOSITIONS AND FABRICATED ARTICLES THEREFROM

The present invention relates to grafted thermoplastic blend compositions and articles fabricated therefrom. The grafting of the polymers generally results in
5 improvements in one or more of melt strength, hardness, modulus, upper service temperature in the resulting blends, over and above what is observed for the corresponding non-grafted blends. Furthermore the grafted blends may in turn be blended with additional thermoplastic polymers to further enhance one or more other properties. The various grafted blend compositions are useful in the preparation of a
10 variety of fabricated articles including, but not limited to, foams, films, fibers, extrusion coatings, calandered and molded articles.

Cross-linking or coupling of polymers has been used as a method of rheology modification of the polymer. As used herein, the term "rheology modification" means change in melt viscosity of a polymer as determined by dynamic mechanical
15 spectroscopy (DMS). Cross-linking is typically employed to increase the melt strength of the polymer while maintaining the high shear viscosity (that is viscosity measured at a shear rate of 100 rad/sec by DMS). Thus a molten cross-linked polymer exhibits more resistance to stretching during elongation at low shear conditions (that is viscosity measured at a shear of 0.1 rad/sec by DMS) and does not sacrifice the output
20 at high shear conditions.

Various coupling agents may be employed to rheology modify and graft polymers. Such coupling agents include peroxides, silanes, and azides. Use of poly(sulfonyl azide) to react with polymers is known, for instance the teachings of US 3,058,944; 3,336,268; and 3,530,108 include the reaction of certain poly(sulfonyl
25 azide) compounds with isotactic polypropylene or other polyolefins by nitrene insertion into C-H bonds. The product reported in US 3,058,944 is crosslinked. The product reported in US 3,530,108 is foamed and cured with cycloalkane-di(sulfonyl azide) of a given formula. In US 3,336,268 the resulting reaction products are referred to as "bridged polymers" because polymer chains are "bridged" with sulfonamide
30 bridges. The disclosed process includes a mixing step such as milling or mixing of the sulfonylazide and polymer in solution or dispersion then a heating step where the

temperature is sufficient to decompose the sulfonylazide (100°C to 225°C depending on the azide decomposition temperature). The starting polypropylene polymer for the claimed process has a molecular weight of at least 275,000. Blends taught in US 3,336,268 have up to about 25 percent ethylene propylene elastomer. Similarly, the teachings of Canadian patent 797,917 include rheology modification using from about 0.001 to 0.075 weight percent polysulfonyl azide to modify homopolymer polyethylene and its blend with polyisobutylene.

It would be highly desirable to have a polymer composition of enhanced melt strength, melt elongation greater than or equal to about 20 mm/s, increased upper service temperature, increased modulus, and increased hardness. Preferably, the polymer compositions would have little or no high shear viscosity increase over a corresponding polymer of the same chemical composition absent coupling agent.

In particular, it would be highly desirable to have a polymer composition of enhanced melt strength, and melt elongation greater than or equal to about 20 mm/s, that can be used to fabricate various articles including foams. Such foams should exhibit at least one of, (1) increased upper service temperature, (2) increased compressive strength at a specific foam density, or (3) increased hardness.

This invention describes grafted blend compositions, processes for their preparation and fabricated articles, especially foams therefrom. The blends exhibit enhanced melt strength, melt elongation greater than or equal to about 20 mm/s, increased upper service temperature, increased modulus, and increased hardness. The grafted blend compositions have little or no high shear viscosity increase over a corresponding polymer of the same chemical composition absent the coupling agent.

Definitions

All references herein to elements or metals belonging to a certain Group refer to the Periodic Table of the Elements published and copyrighted by CRC Press, Inc., 1989. Also any reference to the Group or Groups shall be to the Group or Groups as reflected in this Periodic Table of the Elements using the IUPAC system for numbering groups.

Any numerical values recited herein include all values from the lower value to the upper value in increments of one unit provided that there is a separation of at least 2 units between any lower value and any higher value. As an example, if it is stated that the amount of a component or a value of a process variable such as, for example, temperature, pressure, time is, for example, from 1 to 90, preferably from 20 to 80, more preferably from 30 to 70, it is intended that values such as 15 to 85, 22 to 68, 43 to 51, 30 to 32 etc. are expressly enumerated in this specification. For values which are less than one, one unit is considered to be 0.0001, 0.001, 0.01 or 0.1 as appropriate. These are only examples of what is specifically intended and all possible combinations of numerical values between the lowest value and the highest value enumerated are to be considered to be expressly stated in this application in a similar manner.

The term "interpolymer" is used herein to indicate a polymer wherein at least two different monomers are polymerized to make the interpolymer. This includes copolymers, terpolymers, etc.

The term "melt processing" is used to mean any process in which the polymer is softened or melted, such as extrusion, pelletizing, molding, thermoforming, film blowing, compounding in polymer melt form, fiber spinning.

The term "melt strength" refers to the maximum force attained before significant draw resonance or breakage occurs when pulling strands of molten polymers at constant acceleration until draw resonance or breakage occurred. The velocity at which draw resonance or breakage occurred is defined as the "melt elongation" (the test method is described herein). Unless otherwise specified, both melt strength and melt elongation are measured at 190°C.

As used herein the term "grafted blend composition" means a polymer blend composition further comprising a coupling agent, with the proviso that the resulting grafted blend has a gel content (as determined in accordance with ASTM D-2765-84) which is 50 percent or less, preferably 40 percent or less, more preferably 30 percent or less, even more preferably 20 percent or less, most preferably 10 percent or less.

As used herein the term "alkenyl aromatic homopolymers, or copolymers" include homopolymers and copolymers derived from alkenyl aromatic compounds

such as styrene, alphas-methylstyrene, ethylstyrene, vinyl benzene, vinyl toluene, chlorostyrene, and bromostyrene. A preferred alkenyl aromatic polymer is polystyrene. Minor amounts of monoethylenically unsaturated compounds such as C₂₋₆ alkyl acids and esters, ionomeric derivatives, and C₄₋₆ dienes may be copolymerized with alkenyl aromatic compounds. Examples of copolymerizable compounds include acrylic acid, methacrylic acid, ethacrylic acid, maleic acid, itaconic acid, acrylonitrile, maleic anhydride, methyl acrylate, ethyl acrylate, isobutyl acrylate, n-butyl acrylate, methyl methacrylate, vinyl acetate and butadiene.

For purposes of this invention, an alkenyl aromatic polymer is a melt-processable polymer or melt processable impact-modified polymer having at least 50 percent, preferably at least about 70 percent and most preferably at least 90 percent of its weight in the form of polymerized vinyl aromatic monomers as represented by the structure:



wherein R is hydrogen or an alkyl radical that preferably has no more than three carbon atoms and Ar is an aromatic group. R is preferably hydrogen or methyl, most preferably hydrogen. Suitable aromatic groups Ar include phenyl and naphthyl groups. The aromatic group Ar may be substituted. Halogen (such as Cl, F, Br), alkyl (especially C₁-C₄ alkyl such as methyl, ethyl, propyl and t-butyl), C₁-C₄ haloalkyl (such as chloromethyl or chloroethyl) and alkoxy (such as methoxy or ethoxy) substituents are all useful. Styrene, para-vinyl toluene, α -methyl styrene, 4-methoxy styrene, t-butyl styrene, chlorostyrene, vinyl naphthalene are all useful vinyl or vinylidene aromatic monomers. Most preferably, the alkenyl aromatic polymer material is comprised entirely of alkenyl aromatic monomeric units. Suitable alkenyl aromatic polymers include those derived from alkenyl aromatic compounds such as styrene, alpha-methylstyrene, etc. Examples of copolymerizable compounds include acrylic acid, methacrylic acid, acrylonitrile, etc.

The alkenyl aromatic polymer may be a homopolymer of a vinyl aromatic monomer as described above. Polystyrene homopolymers are the most preferred

alkenyl aromatic polymers. Interpolymers of two or more vinyl aromatic monomers are also useful.

Although not critical, the alkenyl aromatic polymer may be characterized as having a high degree of syndiotactic configuration; that is, the aromatic groups are located alternately at opposite directions relative to the main chain consisting of carbon-carbon bonds. Homopolymers of vinyl aromatic polymers that have syndiotacticity of 75 percent r diad or greater or even 90 percent r diad or greater as measured by ^{13}C NMR are useful herein.

The alkenyl aromatic polymer may also contain repeating units derived from one or more other monomers that are copolymerizable with the vinyl aromatic monomer. Suitable such monomers include N-phenyl maleimide; acrylamide; ethylenically unsaturated nitriles such as acrylonitrile and methacrylonitrile; ethylenically unsaturated carboxylic acids and anhydrides such as acrylic acid, methacrylic acid, fumaric anhydride and maleic anhydride; esters of ethylenically unsaturated acids such as $\text{C}_1\text{-C}_8$ alkyl acrylates and methacrylates, for example n-butyl acrylate and methyl methacrylate; and conjugated dienes such as butadiene or isoprene. The interpolymers of these types may be random, block or graft interpolymers. Blends of interpolymers of this type with homopolymers of a vinyl aromatic monomer can be used. For example, styrene/ $\text{C}_4\text{-C}_8$ alkyl acrylate interpolymers and styrene-butadiene interpolymers are suitable as impact modifiers when blended into polystyrene. Such impact-modified polystyrenes are useful herein.

In addition, suitable alkenyl aromatic polymers include those modified with rubbers to improve their impact properties. The modification can be, for example, through blending, grafting or polymerization of a vinyl aromatic monomer (optionally with other monomers) in the presence of a rubber compound. Examples of suitable rubbers are homopolymers of $\text{C}_4\text{-C}_6$ conjugated dienes such as butadiene or isoprene; ethylene/propylene interpolymers; interpolymers of ethylene, propylene and a nonconjugated diene such as 1,6-hexadiene or ethylidene norbornene; $\text{C}_4\text{-C}_6$ alkyl acrylate homopolymers or interpolymers, including interpolymers thereof with a $\text{C}_1\text{-C}_4$ alkyl acrylate. The rubbers are conveniently prepared by anionic solution

polymerization techniques or by free radical initiated solution, mass or suspension polymerization processes. Rubber polymers that are prepared by emulsion polymerization may be agglomerated to produce larger particles having a multimodal particle size distribution.

5 Preferred impact modified alkenyl aromatic polymers are prepared by dissolving the rubber into the vinyl aromatic monomer and any comonomers and polymerizing the resulting solution, preferably while agitating the solution so as to prepare a dispersed, grafted, impact modified polymer having rubber domains containing occlusions of the matrix polymer dispersed throughout the resulting
10 polymerized mass. In such products, polymerized vinyl aromatic monomer forms a continuous polymeric matrix. Additional quantities of rubber polymer may be blended into the impact modified polymer if desired.

Commercial HIPS (high impact polystyrene), ABS (acrylonitrile-butadiene-styrene) and SAN (styrene-acrylonitrile) resins that are melt processable are also useful
15 as blend components of the present invention.

The alkenyl aromatic polymer has a molecular weight such that it can be melt processed with a blowing agent to form a cellular foam structure. A number average molecular weight of 60,000 to 350,000, preferably from 100,000 to 325,000 is suitable. In the case of an impact-modified polymer, these molecular weight numbers refer to
20 molecular weight of the matrix polymer (that is, the continuous phase polymer of an alkenyl aromatic monomer).


The term "substantially random" (in the substantially random interpolymer comprising polymer units derived from ethylene and one or more α -olefin monomers with one or more vinyl or vinylidene aromatic monomers and/or aliphatic or
25 cycloaliphatic vinyl or vinylidene monomers) as used herein means that the distribution of the monomers of said interpolymer can be described by the Bernoulli statistical model or by a first or second order Markovian statistical model, as described by J. C. Randall in POLYMER SEQUENCE DETERMINATION, Carbon-13 NMR Method, Academic Press New York, 1977, pp. 71-78. Preferably, substantially
30 random interpolymers do not contain more than 15 percent of the total amount of vinyl

aromatic monomer in blocks of vinyl aromatic monomer of more than 3 units. More preferably, the interpolymer is not characterized by a high degree of either isotacticity or syndiotacticity. This means that in the carbon-¹³ NMR spectrum of the substantially random interpolymer the peak areas corresponding to the main chain methylene and methine carbons representing either meso diad sequences or racemic diad sequences should not exceed 75 percent of the total peak area of the main chain methylene and methine carbons.

The "substantially random interpolymers" can be prepared by polymerizing i) ethylene and/or one or more α -olefin monomers and ii) one or more vinyl or vinylidene aromatic monomers and/or one or more sterically hindered aliphatic or cycloaliphatic vinyl or vinylidene monomers, and optionally iii) other polymerizable ethylenically unsaturated monomer(s). Suitable α -olefins includes for example, α -olefins containing from 3 to about 20, preferably from 3 to about 12, more preferably from 3 to about 8 carbon atoms. Particularly suitable are ethylene, propylene, butene-1, 4-methyl-1-pentene, hexene-1 or octene-1 or ethylene in combination with one or more of propylene, butene-1, 4-methyl-1-pentene, hexene-1 or octene-1. These α -olefins do not contain an aromatic moiety.

Other optional polymerizable ethylenically unsaturated monomer(s) include norbornene and C₁₋₁₀ alkyl or C₆₋₁₀ aryl substituted norbornenes, with an exemplary interpolymer being ethylene/styrene/norbornene.

Suitable vinyl or vinylidene aromatic monomers, which can be employed to prepare the interpolymers, include, for example, those represented by the following formula:




wherein R¹ is selected from the group of radicals consisting of hydrogen and alkyl radicals containing from 1 to about 4 carbon atoms, preferably hydrogen or methyl; each R² is independently selected from the group of radicals consisting of hydrogen and alkyl radicals containing from 1 to about 4 carbon atoms, preferably hydrogen or methyl; Ar is a phenyl group or a phenyl group substituted with from 1 to 5

substituents selected from the group consisting of halo, C₁₋₄-alkyl, and C₁₋₄-haloalkyl; and n has a value from zero to about 4, preferably from zero to 2, most preferably zero.

Exemplary vinyl or vinylidene aromatic monomers include styrene, vinyl toluene, α -methylstyrene, t-butyl styrene, chlorostyrene, including all isomers of these

- 5 compounds. Particularly suitable such monomers include styrene and lower alkyl- or halogen-substituted derivatives thereof. Preferred monomers include styrene, α -methyl styrene, the lower alkyl- (C₁ - C₄) or phenyl-ring substituted derivatives of styrene, such as for example, ortho-, meta-, and para-methylstyrene, the ring halogenated styrenes, para-vinyl toluene or mixtures thereof. A more preferred
- 10 aromatic vinyl monomer is styrene.

By the term "sterically hindered aliphatic or cycloaliphatic vinyl or vinylidene compounds", it is meant addition polymerizable vinyl or vinylidene monomers corresponding to the formula:




- 15 wherein A¹ is a sterically bulky, aliphatic or cycloaliphatic substituent of up to 20 carbons, R¹ is selected from the group of radicals consisting of hydrogen and alkyl radicals containing from 1 to about 4 carbon atoms, preferably hydrogen or methyl; each R² is independently selected from the group of radicals consisting of hydrogen and alkyl radicals containing from 1 to about 4 carbon atoms, preferably hydrogen or
- 20 methyl; or alternatively R¹ and A¹ together form a ring system. Preferred aliphatic or cycloaliphatic vinyl or vinylidene compounds are monomers in which one of the carbon atoms bearing ethylenic unsaturation is tertiary or quaternary substituted. Examples of such substituents include cyclic aliphatic groups such as cyclohexyl, cyclohexenyl, cyclooctenyl, or ring alkyl or aryl substituted derivatives thereof, tert-
- 25 butyl, norbornyl. Most preferred aliphatic or cycloaliphatic vinyl or vinylidene compounds are the various isomeric vinyl- ring substituted derivatives of cyclohexene and substituted cyclohexenes, and 5-ethylidene-2-norbornene. Especially suitable are 1-, 3-, and 4-vinylcyclohexene. Simple linear non-branched α -olefins including for example, α -olefins containing from 3 to about 20 carbon atoms such as propylene,

butene-1, 4-methyl-1-pentene, hexene-1 or octene-1 are not examples of sterically hindered aliphatic or cycloaliphatic vinyl or vinylidene compounds.

The substantially random interpolymers include the pseudo-random interpolymers as described in EP-A-0,416,815 by James C. Stevens et al. and US Patent
 5 No. 5,703,187 by Francis J. Timmers. The substantially random interpolymers also include the substantially random terpolymers as described in US Patent No. 5,872,201. The substantially random interpolymers are best prepared by polymerizing a mixture of polymerizable monomers in the presence of one or more metallocene or constrained geometry catalysts in combination with various cocatalysts. Preferred operating
 10 conditions for the polymerization reactions are pressures from atmospheric up to 3000 atmospheres and temperatures from -30°C to 200°C. Polymerizations and unreacted monomer removal at temperatures above the autopolymerization temperature of the respective monomers may result in formation of some amounts of homopolymer polymerization products resulting from free radical polymerization.

15 Examples of suitable catalysts and methods for preparing the substantially random interpolymers are disclosed in U.S. Application Serial No. 702,475, filed May 20, 1991 (EP-A-514,828); as well as U.S. Patents: 5,055,438; 5,057,475; 5,096,867; 5,064,802; 5,132,380; 5,189,192; 5,321,106; 5,347,024; 5,350,723; 5,374,696; 5,399,635; 5,470,993; 5,703,187; and 5,721,185.

20 The substantially random α -olefin/vinyl aromatic interpolymers can also be prepared by the methods described in JP 07/278230 employing compounds shown by the general formula



25 where Cp^1 and Cp^2 are cyclopentadienyl groups, indenyl groups, fluorenyl groups, or substituents of these, independently of each other; R^1 and R^2 are hydrogen atoms, halogen atoms, hydrocarbon groups with carbon numbers of 1-12, alkoxyl groups, or aryloxyl groups, independently of each other; M is a group IV metal, preferably Zr or

Hf, most preferably Zr; and R^3 is an alkylene group or silanediyl group used to cross-link Cp^1 and Cp^2).

The substantially random α -olefin/vinyl aromatic interpolymers can also be prepared by the methods described by John G. Bradfute et al. (W. R. Grace & Co.) in WO 95/32095; by R. B. Pannell (Exxon Chemical Patents, Inc.) in WO 94/00500; and in Plastics Technology, p. 25 (September 1992).

Also suitable are the substantially random interpolymers which comprise at least one α -olefin/vinyl aromatic/vinyl aromatic/ α -olefin tetrad disclosed in U. S. Application No. 08/708,869 filed September 4, 1996 and WO 98/09999 both by Francis J. Timmers et al. These interpolymers contain additional signals in their carbon-13 NMR spectra with intensities greater than three times the peak to peak noise. These signals appear in the chemical shift range 43.70 - 44.25 ppm and 38.0 - 38.5 ppm. Specifically, major peaks are observed at 44.1, 43.9, and 38.2 ppm. A proton test NMR experiment indicates that the signals in the chemical shift region 43.70 - 44.25 ppm are methine carbons and the signals in the region 38.0 - 38.5 ppm are methylene carbons.

Further preparative methods for the interpolymers used in the present invention have been described in the literature. Longo and Grassi (Makromol. Chem., Volume 191, pages 2387 to 2396 [1990]) and D'Anniello et al. (Journal of Applied Polymer Science, Volume 58, pages 1701-1706 [1995]) reported the use of a catalytic system based on methylalumoxane (MAO) and cyclopentadienyltitanium trichloride ($CpTiCl_3$) to prepare an ethylene-styrene copolymer. Xu and Lin (Polymer Preprints, Am. Chem. Soc., Div. Polym. Chem.) Volume 35, pages 686,687 [1994]) have reported copolymerization using a $MgCl_2/TiCl_4/NdCl_3/Al(iBu)_3$ catalyst to give random copolymers of styrene and propylene. Lu et al (Journal of Applied Polymer Science, Volume 53, pages 1453 to 1460 [1994]) have described the copolymerization of ethylene and styrene using a $TiCl_4/NdCl_3/MgCl_2/Al(Et)_3$ catalyst. Sernetz and Mulhaupt, (Macromol. Chem. Phys., v. 197, pp. 1071-1083, 1997) have described the influence of polymerization conditions on the copolymerization of styrene with ethylene using $Me_2Si(Me_4Cp)(N\text{-tert-butyl})TiCl_2$ /methylaluminoxane Ziegler-Natta catalysts. Copolymers of ethylene and styrene produced by bridged metallocene

catalysts have been described by Arai, Toshiaki and Suzuki (Polymer Preprints, Am. Chem. Soc., Div. Polym. Chem.) Volume 38, pages 349, 350 [1997]) and in United States patent number 5,652,315, issued to Mitsui Toatsu Chemicals, Inc. The manufacture of α -olefin/vinyl aromatic monomer interpolymers such as
5 propylene/styrene and butene/styrene are described in United States patent number 5,244,996, issued to Mitsui Petrochemical Industries Ltd or United States patent number 5,652,315 also issued to Mitsui Petrochemical Industries Ltd or as disclosed in DE 197 11 339 A1 to Denki Kagaku Kogyo KK. Also, although of high isotacticity, the random copolymers of ethylene and styrene as disclosed in Polymer Preprints Vol
10 39, No. 1, March 1998 by Toru Aria et al. can also be employed as blend components for the foams of the present invention.

While preparing the substantially random interpolymers, an amount of atactic vinyl aromatic homopolymer may be formed due to homopolymerization of the vinyl aromatic monomer at elevated temperatures. The presence of vinyl aromatic
15 homopolymer is in general not detrimental for the purposes of the present invention and can be tolerated. The vinyl aromatic homopolymer may be separated from the interpolymers, if desired, by extraction techniques such as selective precipitation from solution with a non solvent for either the interpolymers or the vinyl aromatic homopolymer. For the purpose of the present invention it is preferred that no more
20 than 30 weight percent, preferably less than 20 weight percent based on the total weight of the interpolymers of atactic vinyl aromatic homopolymer is present.

The substantially random interpolymers comprise polymer units derived from (1) 0.5 to 65 mole percent of either (a) at least one vinyl or vinylidene aromatic monomer, or (b) at least one hindered aliphatic or cycloaliphatic vinyl or vinylidene
25 monomer, or (c) a combination of at least one vinyl or vinylidene aromatic monomer and at least one hindered aliphatic or cycloaliphatic vinyl or vinylidene monomer; and (2) 35 to 99.5 mole percent of at least one aliphatic α -olefin having from 2 to 20 carbon atoms.

The term "olefinic polymer" as used herein means olefinic polymers comprising
30 the aliphatic C₂-C₂₀ α -olefin homopolymers or interpolymers, or interpolymers of one or more aliphatic α -olefins and one or more non-aromatic monomers

interpolymerizable therewith (such as C_2 - C_{20} α -olefins) or those aliphatic α -olefins having from 2 to 20 carbon atoms and containing polar groups. Suitable aliphatic α -olefin monomers which introduce polar groups into the polymer include, for example, ethylenically unsaturated nitriles such as acrylonitrile, methacrylonitrile, 5 ethacrylonitrile, etc.; ethylenically unsaturated anhydrides such as maleic anhydride; ethylenically unsaturated amides such as acrylamide, methacrylamide etc.; ethylenically unsaturated carboxylic acids (both mono- and difunctional) such as acrylic acid and methacrylic acid, etc.; esters (especially lower, for example, C_1 - C_6 , alkyl esters) of ethylenically unsaturated carboxylic acids such as methyl methacrylate, 10 ethyl acrylate, hydroxyethylacrylate, n-butyl acrylate or methacrylate, 2-ethylhexylacrylate etc.; ethylenically unsaturated dicarboxylic acid imides such as N-alkyl or N-aryl maleimides such as N-phenyl maleimide, etc. Preferably such monomers containing polar groups are acrylic acid, vinyl acetate, maleic anhydride and acrylonitrile. Halogen groups which can be included in the polymers from aliphatic α -olefin monomers include fluorine, chlorine and bromine; preferably such polymers are 15 chlorinated polyethylenes (CPEs).

Preferred olefinic polymers for use in the present invention are homopolymers or interpolymers of an aliphatic, including cycloaliphatic, α -olefin having from 2 to 18 carbon atoms. Suitable examples are homopolymers of ethylene or propylene, and 20 interpolymers of two or more α -olefin monomers. Other preferred olefinic polymers are interpolymers of ethylene and one or more other α -olefins having from 3 to 8 carbon atoms. Preferred comonomers include 1-butene, 4-methyl-1-pentene, 1-hexene, and 1-octene. The olefinic polymers may also contain, in addition to the α -olefin, one or more non-aromatic monomers interpolymerizable therewith. Such 25 additional interpolymerizable monomers include, for example, C_4 - C_{20} dienes, preferably, butadiene or 5 ethylidene-2-norbornene.

The olefinic polymers can be further characterized by their degree of long or short chain branching and the distribution thereof. One class of olefinic polymers are the "branched ethylene homopolymers or interpolymers" generally produced by a high 30 pressure polymerization process using a free radical initiator resulting in the traditional long chain branched low density polyethylene (LDPE). LDPE employed in the present

composition usually has a density of less than 0.94 g/cc (ASTM D 792). Also included in the family of branched homopolymers or interpolymers are the ethylene-vinyl acetate copolymers (EVA), or ethylene-acrylic acid copolymers (EAA).

Another class of olefinic polymers are the "linear ethylene homopolymers or
5 interpolymers" which have an absence of long chain branching, and include the traditional linear low density polyethylene polymers (heterogeneous LLDPE) or linear high density polyethylene polymers (HDPE) made using Ziegler polymerization processes (for example, U.S. Patent No. 4,076,698 (Anderson et al.), sometimes called heterogeneous polymers.

10 Also included are the linear high density polyethylenes (HDPE) which consists mainly of long linear polyethylene chains. The HDPE employed in the present invention usually has a density of at least 0.945 grams per cubic centimeter (g/cc) as determined by ASTM D 792.

Another class of linear ethylene homopolymers or interpolymers is
15 heterogeneous LLDPE, which when employed in the present invention generally has a density of from 0.85 to 0.97 g/cc (ASTM D 792). Preferably the LLDPE is an interpolymer of ethylene and one or more other α -olefins having from 3 to 18 carbon atoms, more preferably from 3-8 carbon atoms. Preferred comonomers include 1-butene, 4-methyl-1-pentene, 1-hexene, and 1-octene.

20 A further class of linear ethylene homopolymers or interpolymers is that of the uniformly branched or homogeneous polymers (for example, homogeneous polyethylene). The homogeneous polymers contain no long chain branches and have only branches derived from the monomers (if having more than two carbon atoms). Homogeneous polymers include those made as described in U.S. Patent 3,645,992
25 (Elston), and those made using so-called single site catalysts in a batch reactor having relatively high olefin concentrations (as described in U.S. Patent Nos. 5,026,798 and 5,055,438 (Canich). The uniformly branched/homogeneous polymers are those polymers in which the comonomer is randomly distributed within a given interpolymer molecule and wherein the interpolymer molecules have a similar ethylene/comonomer
30 ratio within that interpolymer.

The homogeneous LLDPE employed in the present composition generally has a density of from 0.85 to 0.94 g/cc (ASTM D 792). Preferably the LLDPE is an interpolymer of ethylene and one or more other α -olefins having from 3 to 18 carbon atoms, more preferably from 3-8 carbon atoms. Preferred comonomers include 1-butene, 4-methyl-1-pentene, 1-hexene, and 1-octene.

Another class of olefinic polymers are the substantially linear ethylene homopolymers or interpolymers. These polymers have a processability similar to LDPE, but the strength and toughness of LLDPE. The substantially linear ethylene homopolymers or interpolymers are disclosed in U.S. Patent Nos. 5,272,236 and 5,278,272. The substantially linear ethylene homopolymers or interpolymers can be a homopolymer of C_2 - C_{20} olefins, such as ethylene, propylene, 4-methyl-1-pentene, etc., or it can be an interpolymer of ethylene with at least one C_3 - C_{20} α -olefin and/or C_2 - C_{20} acetylenically unsaturated monomer and/or C_4 - C_{18} diolefin. The polymer can also be an interpolymer of ethylene with at least one of the above C_3 - C_{20} α -olefins, diolefins and/or acetylenically unsaturated monomers in combination with other unsaturated monomers. The density of the substantially linear ethylene homopolymers or interpolymers as measured in accordance with ASTM D-792 is generally from 0.85 g/cc to 0.97 g/cc, preferably from 0.85 g/cc to 0.955 g/cc, and especially from 0.85 g/cc to 0.92 g/cc.

Also included in the class of olefinic polymers are the ultra low molecular weight ethylene polymers and ethylene/ α -olefin interpolymers described in the U. S. Patent Application No. 784,683 entitled Ultra-Low Molecular Weight Polymers, filed January 22, 1997 M. J. Guest, et al. These ethylene/ α -olefin interpolymers have I_2 melt indices greater than 1,000, or a number average molecular weight (M_n) less than 11,000.

Also included in the class of olefinic polymers are the various polymeric ionomer compositions including SurlynTM (a product and trademark of Du Pont)

Especially preferred olefinic polymers comprise LDPE, HDPE, heterogeneous LLDPE, homogeneous linear polyethylene, substantially linear olefin polymer, polypropylene (PP), especially isotactic polypropylene, syndiotactic polypropylene and rubber toughened polypropylenes, or ethylene-propylene interpolymers (EP), or

chlorinated polyolefins (CPE), or ethylene-vinyl acetate copolymers (EVA), the polymeric ionomer compositions or ethylene-acrylic acid copolymers, or any combination thereof.

The melt index, measured according to ASTM D-1238, Condition 190°C/2.16 kg (also known as I₂), of the polymer blend component(s) used in the present invention is from 0.01 to 1000, preferably from 0.01 g/10 min. to 100, more preferably from 0.1 to 50, and especially from 0.1 to 10 g/10 min.

The term "coupling agent" or "grafting agent" as used herein interchangeably means a compound or mixture of compounds used for the purposes of coupling or grafting a polymer or polymer blend. The coupling agents used to prepare the grafted compositions of the present invention include, but are not limited to peroxides, silanes, radiation, azides, phenols (as disclosed in USP 4,311,628), aldehyde-amine reaction products (including formaldehyde-ammonia; formaldehyde-ethylchloride-ammonia; acetaldehyde-ammonia; formaldehyde-aniline; butyraldehyde-aniline; and heptaldehyde-aniline), substituted ureas (include trimethylthiourea; diethylthiourea; dibutylthiourea; tripropylthiourea; 1,3-bis(2-benzothiazolylmercaptomethyl)urea; and N,N-diphenylthiourea), substituted guanidines (including diphenylguanidine; di-o-tolylguanidine; diphenylguanidine phthalate; and the di-o-tolylguanidine salt of dicatchol borate); substituted xanthates (including zinc ethylxanthate; sodium isopropylxanthate; butylxanthic disulfide; potassium isopropylxanthate; and zinc butylxanthate); substituted dithiocarbamates (including copper dimethyl-, zinc dimethyl-, tellurium diethyl-, cadmium dicyclohexyl-, lead dimethyl-, lead dimethyl-, selenium dibutyl-, zinc pentamethylene-, zinc didecyl-, and zinc isopropyloctyl-dithiocarbamate); sulfur-containing compounds, such as thiazoles (including 2-mercaptobenzothiazole, zinc mercaptobenzothiazolyl mercaptide, 2-benzothiazolyl-N,N-diethylthiocarbamyl sulfide, and 2,2'-dithiobis(benzothiazole), imidazoles (including 2-mercaptoimidazoline and 2-mercapto-4,4,6-trimethyldihydropyrimidine), sulfenamides (including N-t-butyl-2-benzothiazole-, N-cyclohexylbenzothiazole-, N,N-diisopropylbenzothiazole-, N-(2,6-dimethylmorpholino)-2-benzothiazole-, and N,N-diethylbenzothiazole-sulfenamide)thiuramidisulfides (including N,N'-diethyl-, tetrabutyl-, N,N'-diisopropyldioctyl-, tetramethyl-, N,N'-dicyclohexyl-, and N,N'-

tetralauryl-thiuramidisulfide), paraquinonedioxime, dibenzoparaquinonedioxime, sulfur; and combinations thereof. See Encyclopedia of Chemical Technology, Vol. 17, 2nd edition, Interscience Publishers, 1968; also Organic Peroxides, Daniel Seern, Vol. 1, Wiley-Interscience, 1970),

5 The various coupling technologies are described in U.S. Patent No's 5,869,591 and 5,977,271. Dual cure systems, which use a combination of heat, moisture cure, and radiation steps, may be effectively employed. Dual cure systems are disclosed and claimed in U. S. Patent No. 6,124,370. For instance, it may be desirable to employ peroxide coupling agents in conjunction with silane coupling agents, peroxide coupling
10 agents in conjunction with radiation, sulfur-containing coupling agents in conjunction with silane coupling agents, etc.

Suitable peroxides include aromatic diacyl peroxides; aliphatic diacyl peroxides; dibasic acid peroxides; ketone peroxides; alkyl peroxyesters; alkyl hydroperoxides (for example, diacetylperoxide; dibenzoylperoxide; bis-2,4-
15 dichlorobenzoyl peroxide; di-tert-butyl peroxide; dicumylperoxide; tert-butylperbenzoate; tert-butylcumylperoxide; 2,5-bis (t-butylperoxy)-2,5-dimethylhexane; 2,5-bis (t-butylperoxy)-2,5-dimethylhexyne-3; 4,4,4',4'-tetra-(t-butylperoxy)-2,2-dicyclohexylpropane; 1,4-bis-(t-butylperoxyisopropyl)-benzene; 1,1-bis-(t-butylperoxy)-3,3,5-trimethylcyclohexane; lauroyl peroxide; succinic acid
20 peroxide; cyclohexanone peroxide; t-butyl peracetate; butyl hydroperoxide; etc. Preferred are 2,5-dimethyl-2,5-di-(t-butylperoxy) hexyne-3 and 2,5-dimethyl-2,5-di-(t-butylperoxy) hexane, the former is available as Lupersol™ 130 and the latter as Lupersol™ 101, both trademarks and products of Elf Atochem.

Suitable azide coupling agents include azidoformates, such as
25 tetramethylenebis(azido-formate) (see, also, USP 3,284,421, Breslow, Nov. 8, 1966); aromatic polyazides, such as 4,4'-diphenylmethane diazide (see, also, USP 3,297,674, Breslow et al., Jan. 10, 1967); and the poly(sulfonyl azides), such as p,p'-oxybis-(benzene sulfonyl azide).

The poly(sulfonyl azides) are any compounds having at least two sulfonyl azide
30 groups (-SO₂N₃) reactive with the polymer(s). Preferably the poly(sulfonyl azide)s

have a structure X-R-X wherein each X is SO₂N₃ and R represents an unsubstituted or inertly substituted hydrocarbyl, hydrocarbyl ether or silicon-containing group, preferably having sufficient carbon, oxygen or silicon, preferably carbon, atoms to separate the sulfonyl azide groups sufficiently to permit a facile reaction between the polymer(s) and the sulfonyl azide, more preferably at least 1, more preferably at least 2, most preferably at least 3 carbon, oxygen or silicon, preferably carbon, atoms between functional groups. While there is no critical limit to the length of R, each R advantageously has at least one carbon or silicon atom between X's and preferably has less than about 50, more preferably less than about 30, most preferably less than about 20 carbon, oxygen or silicon atoms. Within these limits, larger is better for reasons including thermal and shock stability. When R is straight-chain alkyl hydrocarbon, there are preferably less than 4 carbon atoms between the sulfonyl azide groups to reduce the propensity of the nitrene to bend back and react with itself. Silicon containing groups include silanes and siloxanes, preferably siloxanes. The term inertly substituted refers to substitution with atoms or groups which do not undesirably interfere with the desired reaction(s) or desired properties of the resulting coupled polymers. Such groups include fluorine, aliphatic or aromatic ether, siloxane as well as sulfonyl azide groups when more than two polyolefin chains are to be joined. Suitable structures include R as aryl, alkyl, aryl alkaryl, arylalkyl silane, siloxane or heterocyclic, groups and other groups which are inert and separate the sulfonyl azide groups as described. More preferably R includes at least one aryl group between the sulfonyl groups, most preferably at least two aryl groups (such as when R is 4,4'-diphenylether or 4,4'-biphenyl). When R is one aryl group, it is preferred that the group have more than one ring, as in the case of naphthylene bis(sulfonyl azides). Poly(sulfonyl)azides include such compounds as 1, 5-pentane bis(sulfonyl azide), 1,8-octane bis(sulfonyl azide), 1,10-decane bis(sulfonyl azide), 1,10-octadecane bis(sulfonyl azide), 1-octyl-2,4,6-benzene tris(sulfonyl azide), 4,4'-diphenyl ether bis(sulfonyl azide), 1,6-bis(4'-sulfonazidophenyl)hexane, 2,7-naphthalene bis(sulfonyl azide), and mixed sulfonyl azides of chlorinated aliphatic hydrocarbons containing an average of from 1 to 8 chlorine atoms and from about 2 to 5 sulfonyl azide groups per molecule, and mixtures thereof. Preferred poly(sulfonyl azide)s include oxy-bis(4-

sulfonylazidobenzene), 2,7-naphthalene bis(sulfonyl azido), 4,4'-bis(sulfonyl azido)biphenyl, 4,4'-diphenyl ether bis(sulfonyl azide) and bis(4-sulfonyl azidophenyl)methane, and mixtures thereof.

Sulfonyl azides are conveniently prepared by the reaction of sodium azide with
5 the corresponding sulfonyl chloride, although oxidation of sulfonyl hydrazines with various reagents (nitrous acid, dinitrogen tetroxide, nitrosonium tetrafluoroborate) has also been used.

Polyfunctional compounds capable of insertions into C-H bonds also include carbene-forming compounds such as salts of alkyl and aryl hydrazones and diazo
10 compounds, and nitrene-forming compounds such as alkyl and aryl azides ($R-N_3$), acyl azides ($R-C(O)-N_3$), azidoformates ($R-O-C(O)-N_3$), sulfonyl azides ($R-SO_2-N_3$), phosphoryl azides ($(RO)_2-(PO)-N_3$), phosphinic azides ($R_2-P(O)-N_3$) and silyl azides (R_3-Si-N_3).

Alternatively, silane coupling agents may be employed. In this regard, any
15 silane that will effectively graft the polymers of this invention can be used. Suitable silanes include unsaturated silanes that comprise an ethylenically unsaturated hydrocarbyl group, such as a vinyl, allyl, isopropenyl, butenyl, cyclohexenyl or γ -(meth)acryloxy allyl group, and a hydrolyzable group, such as, for example, a hydrocarbyloxy, hydrocarbonyloxy, or hydrocarbylamino group. Examples of
20 hydrolyzable groups include methoxy, ethoxy, formyloxy, acetoxy, propionyloxy, and alkyl or arylamino groups. Preferred silanes are the unsaturated alkoxy silanes which can be grafted onto the polymer. These silanes and their method of preparation are more fully described in USP 5,266,627 to Meverden, et al. Vinyl trimethoxy silane (VTMOS), vinyl triethoxy silane, γ -(meth)acryloxy propyl trimethoxy silane and
25 mixtures of these silanes are the preferred silane coupling agents for use in this invention.

The amount of silane coupling agent used in the practice of this invention can vary widely depending upon the nature of the substantially random interpolymer, the silane employed, the processing conditions, the amount of grafting initiator, the
30 ultimate application, and similar factors.

The silane coupling agent is used to graft the polymers of this invention by any conventional method, typically in the presence of a free radical initiator for example peroxides and azo compounds, or by ionizing radiation, etc. Organic initiators are preferred, such as any one of the peroxide initiators, for example, dicumyl peroxide, di-
5 tert-butyl peroxide, t-butyl perbenzoate, benzoyl peroxide, cumene hydroperoxide, t-butyl peroctoate, methyl ethyl ketone peroxide, 2,5-dimethyl-2,5-di(t-butyl peroxy)hexane, lauryl peroxide, and tert-butyl peracetate. A suitable azo compound is azobisisobutyl nitrite.

Those skilled in the art will be readily able to select amounts of initiator
10 employed, with the amount selected taking into account characteristics of the polymers, such as molecular weight, molecular weight distribution, comonomer content, as well as the presence of coupling enhancing coagents, additives (such as oil) etc. Typically, the amount of initiator employed will not exceed that which is required to effect grafting.

15 While any conventional method can be used to silane graft the polymers, one preferred method is blending the two with the initiator in the first stage of a reactor extruder, such as a Buss kneader. The grafting conditions can vary, but the melt temperatures are typically between 160°C and 260°C, preferably between 190°C and 230°C, depending upon the residence time and the half-life of the initiator.

20 Cure is promoted with a coupling catalyst, and any catalyst that will provide this function can be used in this invention. These catalysts generally include organic bases, carboxylic acids, and organometallic compounds including organic titanates and complexes or carboxylates of lead, cobalt, iron, nickel, zinc and tin. Dibutyltindilaurate, dioctyltinmaleate, dibutyltindiacetate, dibutyltindioctoate,
25 stannous acetate, stannous octoate, lead naphthenate, zinc caprylate, cobalt naphthenate. Tin carboxylate, especially dibutyltindilaurate and dioctyltinmaleate, are particularly effective for this invention.

Rather than employing a chemical coupling agent, coupling may be effected by use of radiation. Useful radiation types include electron beam or beta ray, gamma rays,

X-rays, or neutron rays. Radiation is believed to effect coupling by generating polymer radicals which may combine and crosslink. Additional teachings concerning radiation coupling are seen in C. P. Park, "Polyolefin Foam" Chapter 9, Handbook of Polymer Foams and Technology, D. Klemperer and K. C. Frisch, eds., Hanser Publishers, New York (1991), pages 198 - 204.

Radiation dosage depends upon the blend polymer compositions. Those skilled in the art will be readily able to select suitable radiation levels, taking into account such variables as thickness and geometry of the article to be irradiated, as well as to characteristics of the polymers, such as molecular weight, molecular weight distribution, comonomer content, the presence of coupling enhancing coagents, additives (such as oil), etc. Typically, the dosage will not exceed that which is required to effect the desired level of coupling.

The choice of coupling agent will depend on the types of polymers being grafted. The coupling agent may be added in a variety of ways. For instance, powder or liquid or pellets may be added to and/or tumble blended with one or more of the blend polymer components which have preferably (but not necessarily) been surface treated with tackifiers. Tackifiers can be obtained by the polymerization of petroleum and terpene feedstreams and from the derivatization of wood, gum, and tall oil rosin. Several classes of tackifiers include wood rosin, tall oil and tall oil derivatives, and cyclopentadiene derivatives, such as are described in United Kingdom patent application GB 2,032,439A. Other classes of tackifiers include aliphatic C₅ resins, polyterpene resins, hydrogenated resins, mixed aliphatic-aromatic resins, rosin esters, natural and synthetic terpenes, terpene-phenolics, and hydrogenated rosin esters. A preferred tackifier is mineral oil.

Alternatively, the coupling agent is dispersed in a suitable non-reactive liquid or tackifier (such as mineral oil) which is then tumble blended with one or more of the blend polymer components. It is especially preferred that the oil is of a room temperature viscosity such that it has sufficient flow to completely wet the surface of

the pellets, and yet be sufficiently viscous such it does not drain quickly on standing prior to feeding to the extruder. A preferred oil is the white mineral oil, Drakeol™ 34 (a registered trademark and product of The Pennzoil Company). The dispersion of coupling agent in non-reactive liquid may also be injected into a melt processing equipment (such as an extruder) used to make the grafted blend compositions.

The amount of non-reactive liquid or tackifier (such as mineral oil) used will vary, and typically is in the range of 0.2-2.0 wt percent (but this is not limiting). Alternatively, the coupling agent may first be compounded in a suitable thermoplastic polymer and pellets, etc of the compound may then be tumble blended with the other blend components before reactive extrusion or independently fed to the extruder.

Those skilled in the art will be readily able to select amounts of coupling agent, with the amount selected taking into account characteristics of the polymer(s) such as molecular weight, molecular weight distribution, comonomer content, the presence of coupling enhancing coagents, additives (such as oil) etc. Since it is expressly contemplated that the polymer(s) may be blended prior to coupling, those skilled in the art may use the following guidelines as a reference point in optimizing the amount of coupling agent preferred for the particular blends in question. Typically, the amount of coupling agent employed will not exceed that which is required to effect the desired level of coupling.

To graft, the coupling agent is used in an amount effective to result in the formation of 50 percent or less, preferably 40 percent or less, more preferably 30 percent or less, even more preferably 20 percent or less, most preferably 10 percent or less weight percent gel as evidenced by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84. This amount may vary depending on the type of the coupling agent, but is generally less than about 2.0, preferably less than about 1.0, more preferably less than about 0.5, most preferably less than about 0.2 weight percent coupling agent (based on the total weight of coupling agent and polymer blend components), with these values depending on the molecular weight of the coupling agent and the molecular weight or melt index of polymers.

The coupling agent and blend are mixed at a first temperature which is at least the melting point of the lowest melting component of the blend and, after mixing, are heated to react at a second temperature which is at least greater than the first temperature and is usually greater than 100°C and most frequently greater than 150°C.

- 5 The preferred temperature range depends on the nature of the coupling agent that is used. For example, in the case of azides (including but not limited to 4,4'-disulfonylazidediphenylether) and peroxides (including but not limited to 2,5-bis (t-butylperoxy)-2,5-dimethylhexyne-3), the preferred temperature range is greater than 150°C, preferably greater than 160°C, more preferably greater than 185°C, most
10 preferably greater than 190°C. Preferably, the upper temperature is less than 300°C.

Temperatures for use in the practice of the invention are also determined by the softening or melt temperatures of the polymer starting materials. For these reasons, the temperature is advantageously greater than about 90°C, preferably greater than about 120°C, more preferably greater than about 150°C, and most preferably greater than
15 170°C.

We have also surprisingly found that further improvements in melt strength of the coupled blends may be achieved by reacting at temperatures greater than or equal to 240°C, more preferably greater than or equal to 250°C even more preferably greater than or equal to 260°C.

- 20 Preferred times at the desired decomposition temperatures are times that are sufficient to result in complete reaction of the coupling agent with the polymer(s). Preferred reaction times in terms of the half-life of the coupling agent (that is the time required for about half of the agent to be reacted at a preselected temperature, and determinable by DSC) is about 5 half-lives of the coupling agent. In the case of a
25 bis(sulfonyl azide), for instance, the reaction time is preferably at least about 4 minutes at 200°C.

Admixing of the polymer and coupling agent is conveniently accomplished by any means within the skill in the art. Desired distribution is different in many cases, depending on what properties are to be modified. In a blend it is often desirable to have
30 low solubility in one or more of the polymer matrices such that the coupling agent is

preferentially in the other phase, or predominantly in the interfacial region between the two phases.

Treatment of blends with the coupling agent according to practice of the invention results in blends of the invention, which are referred to herein as grafted
5 blends. A blend is advantageously mixed with a coupling agent above the softening temperature of at least one component of the blend, most preferably below the peak decomposition temperature of the coupling agent, and the resulting mixture is preferably raised to at least the peak decomposition temperature of the coupling agent.

Practice of the invention advantageously involves forming a substantially
10 uniform admixture of polymers and coupling agent (before its decomposition). In the case of blends where there are dispersed and continuous phases, it may be sufficient for the coupling agent to be dispersed at the interface of the phases rather than being uniformly distributed.

Processes for coupling include at least one of (a) dry blending the coupling
15 agent with the polymer, preferably to form a substantially uniform admixture and adding this mixture to melt processing equipment, for example, a melt extruder to achieve the coupling reaction, at a temperature at least the decomposition temperature of the coupling agent; (b) introducing, for example, by injection, a coupling agent in liquid form, for example, dissolved in a solvent therefor or in a slurry of coupling
20 agent in a liquid, into a device containing polymer, preferably softened, molten or melted polymer, but alternatively in particulate form, in solution or dispersion, more preferably in melt processing equipment; (c) forming a first admixture of a first amount of a first polymer and a coupling agent, advantageously at a temperature less than about the decomposition temperature of the coupling agent, preferably by melt
25 blending, and then forming a second admixture of the first admixture with a second amount of a second polymer (for example a concentrate of a coupling agent admixed with at least one polymer and optionally other additives, is conveniently admixed into a second polymer or combination thereof optionally with other additives, to modify the second polymer(s)); (d) feeding at least one coupling agent, preferably in solid form,
30 more preferably finely comminuted, for example, powder, directly into softened or

molten polymer, for example, in melt processing equipment, for example, in an extruder; or combinations thereof.

Process (c) is conveniently used to make a concentrate with a first polymer composition having a lower melting temperature, advantageously at a temperature
5 below the decomposition temperature of the coupling agent, and the concentrate is melt blended into a second polymer composition having a higher melting temperature to complete the coupling reaction.

Concentrates are especially preferred when temperatures are sufficiently high to result in loss of coupling agent by evaporation or decomposition not leading to reaction
10 with the polymer, or other conditions would result that effect. Alternatively, some coupling occurs during the blending of the first polymer and coupling agent, but some of the coupling agent remains unreacted until the concentrate is blended into the second polymer composition. The polymer composition optionally includes additives known within the skill in the art. When the coupling agent is added in a dry form it is
15 preferred to mix the agent and polymer in a softened or molten state below the decomposition temperature of the coupling agent then to heat the resulting admixture to a temperature at least equal to the decomposition temperature of the coupling agent.

The polyolefin(s) and coupling agent are suitably combined in any manner which results in desired reaction thereof, preferably by mixing the coupling agent with
20 the polymer(s) under conditions which allow sufficient mixing before reaction to avoid uneven amounts of localized reaction then subjecting the resulting admixture to heat sufficient for reaction. Preferably, a substantially uniform admixture of coupling agent and polymer is formed before exposure to conditions in which chain coupling takes place.

25 A substantially uniform admixture is one in which the distribution of coupling agent in the polymer is sufficiently homogeneous to be evidenced by a polymer having a melt viscosity after treatment according to the practice of the invention either higher at low angular frequency (for example, 0.1 rad/sec) or lower at higher angular frequency (for example, 100 rad/sec) than that of the same polymer which has not been
30 treated with the coupling agent but has been subjected to the same shear and thermal history.

Thus, preferably, in the practice of the invention, decomposition of the coupling agent occurs after mixing sufficient to result in a substantially uniform admixture of coupling agent and polymer. This mixing is preferably attained with the polymer in a molten or melted state, which is above the crystalline melt temperature, or
5 in a dissolved or finely dispersed condition rather than in a solid mass or particulate form. The molten or melted form is more preferred to insure homogeneity rather than localized concentrations at the surface.

While any equipment can be suitably used, equipment which provides sufficient mixing and temperature control in the same equipment, including such
10 devices as an extruder, or a static polymer mixing device such as a Brabender blender, are preferred. The term extruder is used in its broadest meaning to include such devices as those, which extrude pellets such as a pelletizer.

In one embodiment of the invention, the grafting process takes place in a single vessel, that is mixing of the coupling agent and polymer takes place in the same vessel
15 as heating to the decomposition temperature of the coupling agent. The vessel is preferably an extruder, which may optionally be suitable for foam preparation. The reaction vessel more preferably has at least two zones of different temperatures into which a reaction mixture passes. The first zone advantageously is at a temperature of at least the crystalline melt temperature or the softening temperature of the polymer(s)
20 and preferably less than the decomposition temperature of the coupling agents, with the second zone being at a temperature sufficient for decomposition of the coupling agent. The first zone is preferably at a temperature sufficiently high to soften the polymer and allow it to combine with the coupling agent, through distributive mixing to a substantially uniform admixture. Addition of a blowing agent may optionally occur in
25 either of these zones, depending on the temperatures advantageous for its use.

In one embodiment the foam forming step or steps and the grafting steps are at least partially simultaneous. Thus the coupling agent is introduced during any step
before or in a foam forming process that is of a temperature sufficiently low to result in adequate mixing before or during grafting and grafting takes place in or simultaneous
30 with any step in a foam forming process in which the temperature is at least about the decomposition temperature of the coupling agent. Grafting, however, preferably takes

place before the foam is extruded or otherwise exits the vessel in which the polymer is admixed with any blowing agent.

For polymers that have softening points above the coupling agent decomposition temperature (preferably greater than 200°C), and especially when
5 incorporation of a lower melting polymer (such as in a concentrate) is undesirable, the preferred method for incorporation of coupling agent is to solution blend the coupling agent in solution or admixture into the polymer, (this allows the polymer to imbibe that is absorb or adsorb at least some of the coupling agent), and then to evaporate the solvent. After evaporation, the resulting mixture is extruded. The solvent is preferably
10 a solvent for the coupling agent, and more preferably also for the polymer when the polymer is soluble such as in the case of polycarbonate. Such solvents include polar solvents such as acetone, THF (tetrahydrofuran) and chlorinated hydrocarbons such as methylene chloride. Alternatively other non-polar compounds such as mineral oils in which the coupling agent is sufficiently miscible to disperse the coupling agent in a
15 polymer, are used.

The present invention can be summarized in terms of the following embodiments:

Embodiment One

In one embodiment of the present invention, it has been found that the melt
20 strength, hardness and/or upper service temperature of certain blend compositions comprising, (A) one or more homopolymers or interpolymers with peak crystalline melting temperature (T_m) and/or glass transition temperature (T_g by DSC) of 90°C or more; (B) one or more homopolymers or interpolymers with peak crystalline melting temperature (T_m) and/or glass transition temperature (T_g by DSC) of 80°C or less; can
25 be increased significantly by grafting with (C) at least one coupling agent, preferably an azide or peroxide.

These blends of Embodiment One can comprise a grafted blend of

- 1) two or more substantially random interpolymers;
- 2) two or more olefinic polymers;
- 30 3) two or more alkenyl aromatic polymers

- 4) one or more substantially random interpolymers and one or more olefinic polymers;
- 5) one or more substantially random interpolymers, and one or more alkenyl aromatic polymers; or
- 5 6) one or more olefinic polymers, and one or more alkenyl aromatic polymers; or
- 7) one or more substantially random interpolymers, and one or more alkenyl aromatic polymers; or
- 8) one or more olefinic polymers, one or more substantially random
10 interpolymers and one or more alkenyl aromatic polymers.

The resulting blends exhibit a more than additive increase in melt strength. This improvement is believed to result from the coupling agent reacting with more than one polymer chain to connect them, referred to herein as "grafting". Grafting results in rheology modification, that is, change in melt viscosity of a polymer as
15 determined by dynamic mechanical spectroscopy. The blends of Embodiment One advantageously have increased melt strength and are thus useful in making fibers, film and foams.

The blends of this invention will have upper service temperature greater than 80°C, preferably greater than 85°C and most preferably greater than 90°C.

20 The blends will comprise: (A) from 0.5 to 99.5, preferably from 5 to 95, more preferably from 10 to 90, most preferably from 10 to 60 weight percent (based on the combined weights of components A and B) of one or more homopolymers or interpolymers with peak crystalline melting temperature (T_m) and/or glass transition temperature (T_g by DSC) of 90°C or more; and (B) from 0.5 to 99.5, preferably from 5
25 to 95, more preferably from 10 to 90, most preferably from 40 to 90 weight percent (based on the combined weights of components A and B) of one or more homopolymers or interpolymers with peak crystalline melting temperature (T_m) and/or glass transition temperature (T_g by DSC) of 80°C or less; and (C) one or more coupling agents.

30 The resulting grafted blend has (1) a gel content which is 50 percent or less, preferably 40 percent or less, more preferably 30 percent or less, even more preferably 20

percent or less, most preferably 10 percent or less as determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84, (2) an increase in melt strength of 5 percent or more, preferably 10 percent or more relative to the same polymer blend without the coupling agent; and (3) an increase in upper service
5 temperature (as measured by Thermal Mechanical Analyses (TMA)) of 0.5°C or more, preferably 1.0°C or more, more preferably 1.5°C or more, even more preferably 5°C or more relative to the same polymer blend without the coupling agent..

The resulting grafted blend also has a melt elongation greater than or equal to about 20 mm/s, preferably greater than or equal to about 25 mm/s, more preferably
10 greater than or equal to about 30 mm/s.

Embodiment Two

We have also surprisingly found grafted blend compositions that exhibit a unique combination of high melt strength, high melt elongation and high flexural modulus.

15 The final grafted blend compositions comprise either; (A) one or more linear or substantially linear ethylene homopolymers or interpolymers and one or more branched ethylene homopolymers or interpolymers; or (B) one or more linear or substantially linear ethylene homopolymers or interpolymers and one or more substantially random interpolymers; or (C) one or more linear or substantially linear ethylene homopolymers
20 or interpolymers, one or more branched ethylene homopolymers or interpolymers and one or more substantially random interpolymers; all of which blends are grafted with (D) one or more coupling agents.

The final grafted blend compositions exhibit high melt strength, that is values greater than about 8, preferably greater than about 10, more preferably greater than
25 about 15 cN.

The final grafted blend compositions also have high melt elongation, that is values of 20 mm/s or greater, preferably 25 mm/s or greater.

The final grafted blend compositions also have high flexural modulus, that is values of 80,000 psi or greater, preferably 100,000 psi or greater, most preferably
30 110,000 psi or greater.

The final grafted blend compositions also have a gel content which is 50 percent or less, preferably 40 percent or less, more preferably 30 percent or less, even more preferably 20 percent or less, most preferably 10 percent or less as determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84.

5 Even more preferably, the gel content of the present grafted blend composition is 10 or less, preferably 5 or less, more preferably 2 or less weight percent gel as evidenced by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84.

10 Preferably these compositions comprise a grafted blend of heterogeneous or homogeneous LLDPE with LDPE, or HDPE with LDPE, or a substantially linear ethylene homopolymer or interpolymer with LDPE.

The coupling agent is preferably an azide or peroxide or combination thereof.

Embodiment Three

15 In another embodiment of the present invention, it has been surprisingly found that certain grafted blend compositions comprising polypropylene are able to exhibit high melt strength while retaining acceptably high flexural modulus (50,000 psi or greater).

20 The grafted blend compositions comprise (A) one or more olefinic polymers other than polypropylene; (B) one or more propylene homopolymers or interpolymers; and (C) at least one coupling agent, preferably an azide or peroxide.

The resulting grafted blend composition has a gel content which is 50 percent or less, preferably 40 percent or less, more preferably 30 percent or less, even more preferably 20 percent or less, most preferably 10 percent or less as determined by
25 insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84.

The resulting grafted blend composition has a melt strength greater than about 5, preferably greater than about 10, more preferably greater than about 15 cN.

The resulting grafted blend also has a melt elongation greater than or equal to about 20 mm/s, preferably greater than or equal to about 25 mm/s.

30 The resulting grafted blend composition has a flexural modulus of 50,000 psi or greater.

Blends and Fabricated Articles Made from the Grafted Blends of Embodiments One to Three

The present invention also includes blends and any fabricated article, which
5 comprise any of the grafted blends of Embodiments One to Three. The blends and
fabricated articles will comprise 0.05 to 100, preferably 0.1 to 100 and most preferably
0.2 to 100 weight percent of the grafted blends of Embodiments 1-3 (based on total
amount of polymers present in the final blend or fabricated article).

The grafted blends of the various embodiments of the present invention may be
10 advantageously used to produce a wide range of fabricated articles including foams,
calendared, cast and blown sheets and films, compression and injection molded parts,
rotational molded parts, fibers. The blends are also useful in applications such as
modifiers for bitumen and asphalt compositions, as components for hot melt and
pressure sensitive adhesive systems, extrusion coating, blowmolding, high speed fiber
15 spinning, oriented nonwovens, thermoforming, labels, candy wrappers, geomembranes,
cereal liners, wire and cable, pipes, etc. Preferably the article is formed from a melt of
the composition. More preferably it is formed by a melt process.

Blending the grafted blends of the aforementioned Embodiments 1-3 with one
or more other thermoplastics provides additional improvements in properties including
20 but not limited to upper service temperature, modulus, compressive strength, hardness,
toughness, increased foam cell size, and aesthetics of the final fabricated articles
(depending on if the graft or other thermoplastic is the predominant blend component).

Examples of the other thermoplastic include, but are not limited to, ethylene
styrene interpolymers (ESI), ethylene vinylacetate copolymers (EVA), polypropylene
25 (PP), polystyrene (PS), high density polyethylene (HDPE), low density polyethylene
(LDPE), and linear low density polyethylene (LLDPE). In one embodiment, grafted
blends of the aforementioned Embodiments 1-3, may be further blended with alkenyl
aromatic polymers (such as polystyrene) to make, for example, alkenyl aromatic
polymer foams with increased cell size.

30 The grafted blends or their blends with other thermoplastics may be prepared
by any suitable means known in the art such as, for example, dry blending in a

pelletized form in desired proportions followed by melt blending in an apparatus such as a screw extruder or a Banbury mixer. Dry blended pellets may be directly melt processed into a final solid state article by, for example, injection molding. The blends may also be made by direct polymerization without isolating blend components.

- 5 Direct polymerization may use, for example, one or more catalysts in a single reactor or two or more reactors in series or parallel and vary at least one of operating conditions, monomer mixtures and catalyst choice.

Various additives may optionally be incorporated into the blend compositions or fabricated articles of the present invention. The additives include, without
10 limitation, stability control agents (specifically for foams), nucleating agents (specifically for foams), inorganic fillers, conductive fillers, pigments, colorants, antioxidants, acid scavengers, ultraviolet absorbers or stabilizers, flame retardants, processing aids, extrusion aids, anti-static agents, cling additives (for example, polyisobutylene), antiblock additives, other thermoplastic polymers. Certain of the additives,
15 such as inorganic and conductive fillers, may also function as nucleating agents and/or open cell promoters for foams. Examples of antioxidants are hindered phenols (such as, for example, Irganox™ 1010) and phosphites (for example, Irgafos™ 168) both trademarks of, and commercially available from, Ciba Geigy Corporation.

The additives are advantageously employed in functionally equivalent amounts
20 known to those skilled in the art. For example, the amount of antioxidant employed is that amount which prevents the polymer or polymer blend from undergoing oxidation at the temperatures and environment employed during storage and ultimate use of the polymers. Such amount of antioxidants is usually in the range of from 0.01 to 10, preferably from 0.02 to 5, more preferably from 0.03 to 2 percent by weight based
25 upon the weight of the polymer or polymer blend. Similarly, the amounts of any of the other enumerated additives are the functionally equivalent amounts such as the amount to render the polymer or polymer blend antiblocking, the desired amount of filler loading to produce the desired result, to provide the desired color from the colorant or pigment. Such additives are advantageously employed in the range of from 0.01 to 90,
30 preferably from 0.02 to 70, more preferably from 0.05 to 50 percent by weight based upon the weight of the polymer or polymer blend.

In the case of foams, a nucleating agent is optionally added in order to control the size of foam cells. Preferred nucleating agents include inorganic substances such as calcium carbonate, talc, clay, titanium oxide, silica, barium stearate, barium sulfate, diatomaceous earth, mixtures of citric acid and sodium bicarbonate. When used, the amount of nucleating agent employed may range from > 0 to about 5 parts by weight per hundred parts by weight of polymer (phr).

In the case of foams, a stability control agent (also known as permeability modifier) is optionally added to the present foam to enhance dimensional stability. Preferred agents include amides and esters of C₁₀₋₂₄ fatty acids. Such agents are seen in U.S. Pat. Nos. 3,644,230 and 4,214,054. Esters may also reduce static during and after foam manufacture. Most preferred agents include stearyl stearamide, glyceromonostearate, glycerol monobehenate, and sorbitol monostearate. When used, such stability control agents are typically employed in an amount ranging from > 0 to about 10 parts per hundred parts of the polymer.

The blend compositions or fabricated articles made from the grafted blends of this invention may be substantially free of crosslinking (that is, contain 50 percent or less, preferably 40 percent or less, more preferably 30 percent or less, even more preferably 20 percent or less, most preferably 10 percent or less weight percent gel based upon total weight of polymer, as measured according to ASTM D-2765-84, Method A).

Alternatively, the grafted blend compositions could be used to make blends or or fabricated articles which are substantially cross-linked (that is, contain greater than 45 weight percent gel based upon the total weight of polymer, as measured according to ASTM D-2765-84 Method A) by further addition of any known cross-linking agent.

The term "cross-linking agent" as used herein means a compound or mixture of compounds used for the purposes of substantially crosslinking a polymer or polymer blend. The cross-linking agent used to prepare the compositions and articles of the present invention include, but are not limited to peroxides, silanes, radiation, azides, phenols, aldehyde-amine reaction products, substituted ureas, substituted guanidines, substituted xanthates, substituted dithiocarbamates, sulfur-containing compounds,

thiazoles, imidazoles, sulfenamides, thiuramidisulfides, paraquinonedioxime, dibenzoparaquinonedioxime, sulfur; and combinations thereof.

The various crosslinking technologies are described in U.S. Patent No's 5,869,591 and 5,977,271, the entire contents of both of which are herein. Dual cure systems, which use a combination of heat, moisture cure, and radiation steps, may be effectively employed. Dual cure systems are disclosed and claimed in U. S. Patent No. 6,124,370. For instance, it may be desirable to employ peroxide coupling agents in conjunction with silane coupling agents, peroxide coupling agents in conjunction with radiation, sulfur-containing coupling agents in conjunction with silane coupling agents, etc.

The blend compositions described above may be converted to foam products using any conventional process. Foam products include, for example, extruded thermoplastic polymer foam, extruded polymer strand foam, expandable thermoplastic foam beads, expanded thermoplastic foam beads or expanded and fused thermoplastic foam beads, and various types of crosslinked foams. The foam products may take any known physical configuration, such as sheet, round, strand geometry, rod, solid plank, laminated plank, coalesced strand plank, profiles and bun stock. The foam products may be converted into fabricated articles using any conventional process or method. For example, any one or more of expansion, coalescing and welding may be used in making such articles, especially from expandable foam beads. One may also mold expandable beads into any known configuration that employs foam products, including, but not limited to the foregoing configurations.

Foam forming steps of the process are known in the art. For instance as exemplified by the excellent teachings to processes for making ethylenic polymer foam structures and processing them in C. P. Park. "Polyolefin Foam", Chapter 9, Handbook of Polymer Foams and Technology, edited by D. Klempner and K. C. Frisch, Hanser Publishers, Munich, Vienna, New York, Barcelona (1991), which is incorporated here in by reference.

Foams of the present invention may be substantially noncrosslinked. The foam structure contains 50 or less, preferably 40 or less, more preferably 30 or less, even more preferably 20 or less, most preferably 10 or less weight percent gel based upon

the total weight of foam or polymer, as measured according to ASTM D-2765-84, Method A.

The foam structure may optionally be substantially cross-linked (that is, greater than 50 percent gel based upon the total weight of foam or polymer, as measured according to ASTM D-2765-84 Method A). The various crosslinking technologies are described in U.S. Patent No's 5,869,591 and 5,977,271, the entire contents of both of which are herein. Dual cure systems, which use a combination of heat, moisture cure, and radiation steps, may be effectively employed. Dual cure systems are disclosed and claimed in U. S. Patent No. 6,124,370. For instance, it may be desirable to employ peroxide coupling agents in conjunction with silane coupling agents, peroxide coupling agents in conjunction with radiation, sulfur-containing coupling agents in conjunction with silane coupling agents, etc. Cross-linking may be induced by addition of a cross-linking agent. Induction of cross-linking and exposure to an elevated temperature to effect foaming or expansion may occur simultaneously or sequentially. If a chemical cross-linking agent is used, it is incorporated into the polymer material in the same manner as the chemical blowing agent. Further, if a chemical cross-linking agent is used, the foamable melt polymer material is heated or exposed to a temperature of preferably less than 150°C to prevent decomposition of the cross-linking agent or the blowing agent and to prevent premature cross-linking. If radiation cross-linking is used, the foamable melt polymer material is heated or exposed to a temperature of preferably less than 160°C to prevent decomposition of the blowing agent. The foamable melt polymer material is extruded or conveyed through a die of desired shape to form a foamable structure. The foamable structure is then cross-linked and expanded at an elevated or high temperature (typically, 150°C-250°C) such as in an oven to form a foam structure. If radiation cross-linking is used, the foamable structure is irradiated to cross-link the polymer material, which is then expanded at the elevated temperature as described above. The present structure can advantageously be made in sheet or thin plank form according to the above process using either cross-linking agents or radiation.

The foam structures of the present invention are optionally made by a conventional extrusion foaming process. The structure is advantageously prepared by

heating the polymer or blend to form a plasticized or melt polymer material, incorporating therein a blowing agent to form a foamable gel, and extruding the gel through a die to form the foam product. Depending upon the die (with an appropriate number of apertures) and operating conditions, the product may vary from an extruded foam plank or rod through a coalesced foam strand product, to foam beads and eventually to chopped strands of foamable beads. Prior to mixing with the blowing agent, the polymer material is heated to a temperature at or above its glass transition temperature or melting point. The blowing agent is optionally incorporated or mixed into the melt polymer material by any means known in the art such as with an extruder, mixer, blender, or the like. The blowing agent is mixed with the melt polymer material at an elevated pressure sufficient to prevent substantial expansion of the melt polymer material and to advantageously disperse the blowing agent homogeneously therein. Optionally, a nucleator is optionally blended in the polymer melt or dry blended with the polymer material prior to plasticizing or melting. Prior to extruding foamable gel through the die, one typically cools the gel to an optimum temperature. The foamable gel is typically cooled to a lower temperature to optimize physical characteristics of the foam structure. This temperature, often referred to as the foaming temperature, is typically above each component's polymer glass transition temperature (T_g), or for those having sufficient crystallinity, near the peak crystalline melting temperature (T_m). "Near" means at, above, or below and largely depends upon where stable foam exists. The temperature desirably falls within 30° centigrade (°C) above or below the T_m . For foams of the present invention, an optimum foaming temperature is in a range in which the foam does not collapse. The gel may be cooled in the extruder or other mixing device or in separate coolers. The gel is then extruded or conveyed through a die of desired shape to a zone of reduced or lower pressure to form the foam structure. The zone of lower pressure is at a pressure lower than that in which the foamable gel is maintained prior to extrusion through the die. The lower pressure is optionally superatmospheric or subatmospheric (vacuum), but is preferably at an atmospheric level.

In another embodiment, the resulting foam structure is optionally formed in a coalesced strand form by extrusion of the polymer material through a multi-orifice die.

The orifices are arranged so that contact between adjacent streams of the molten extrudate occurs during the foaming process and the contacting surfaces adhere to one another with sufficient adhesion to result in a unitary foam structure. The streams of molten extrudate exiting the die take the form of strands or profiles, which desirably foam, coalesce, and adhere to one another to form a unitary structure. Desirably, the coalesced individual strands or profiles should remain adhered in a unitary structure to prevent strand delamination under stresses encountered in preparing, shaping, and using the foam. Apparatuses and method for producing foam structures in coalesced strand form are seen in U.S. Pat. Nos. 3,573,152 and 4,824,720.

Alternatively, the resulting foam structure is conveniently formed by an accumulating extrusion process and apparatus as seen in U.S. Pat. No. 4,323,528 and USP 5,817,705. This apparatus, commonly known as an "extruder-accumulator system" allows one to operate a process on an intermittent, rather than a continuous, basis. The apparatus includes a holding zone or accumulator where foamable gel remains under conditions that preclude foaming. The holding zone is equipped with an outlet die that opens into a zone of lower pressure, such as the atmosphere. The die has an orifice that may be open or closed, preferably by way of a gate that is external to the holding zone. Operation of the gate does not affect the foamable composition other than to allow it to flow through the die. Opening the gate and substantially concurrently applying mechanical pressure on the gel by a mechanism (for example, a mechanical ram) forces the gel through the die into a zone of lower pressure. The mechanical pressure is sufficient to force foamable gel through the die at a rate fast enough to preclude significant foaming within the die yet slow enough to minimize and preferably eliminate generation of irregularities in foam cross-sectional area or shape. As such, other than operating intermittently, the process and its resulting products closely resemble those made in a continuous extrusion process.

In this process, low density foam structures having large lateral cross-sectional areas are prepared by: 1) forming under pressure a gel of the polymer or blend material and a blowing agent at a temperature at which the viscosity of the gel is sufficient to retain the blowing agent when the gel is allowed to expand; 2) extruding the gel into a holding zone maintained at a temperature and pressure which does not allow the gel to

foam, the holding zone having an outlet die defining an orifice opening into a zone of lower pressure at which the gel foams, and an openable gate closing the die orifice; 3) periodically opening the gate; 4) substantially concurrently applying mechanical pressure by a movable ram on the gel to eject it from the holding zone through the die orifice into the zone of lower pressure, at a rate greater than that at which substantial foaming in the die orifice occurs and less than that at which substantial irregularities in cross-sectional area or shape occurs; and 5) permitting the ejected gel to expand unrestrained in at least one dimension to produce the foam structure.

The present foam structures may also be formed into foam beads suitable for molding into articles by expansion of pre-expanded beads containing a blowing agent. The beads may be molded at the time of expansion to form articles of various shapes. Processes for making expanded beads and molded expanded beam foam articles are described in Plastic Foams, Part II, Frisch And Saunders, pp. 544-585, Marcel Dekker, Inc. (1973) and Plastic Materials, Brydson, 5th Ed., pp. 426-429, Butterworths (1989). Expandable and expanded beads can be made by a batch or by an extrusion process, and may be substantially non-crosslinked or substantially crosslinked.

The batch process of making expandable beads is similar to manufacturing expandable polystyrene (EPS). The resulting foam structure is formed into non-crosslinked foam beads suitable for molding into articles. Discrete resin particles, such as granules made from the blends of the present invention, made either by melt blending or in-reactor blending, are impregnated with a blowing agent (and optionally a cross-linking agent) in an aqueous suspension or in an anhydrous state in a pressure vessel at an elevated temperature and pressure. In the case of the aqueous suspension, the blowing agent (and, optionally, cross-linking agent) is/are introduced into the liquid medium in which the granules are substantially insoluble (such as water) at an elevated pressure and temperature in an autoclave or other pressure vessel. The granules are either discharged rapidly into an atmosphere or a region of reduced pressure to expand the granules into foam beads or cooled and discharged as unexpanded beads. In a separate step, the unexpanded beads are heated to expand them, for example, with steam or with hot air. This process for making bead foams is well taught in U.S. Pat. Nos. 4,379,859 and 4,464,484.

In a modification of the bead process, styrene monomer is optionally impregnated into the suspended pellets of the blend compositions of the present invention prior to their impregnation with blowing agent to form a graft interpolymer with the polymer material. The resulting interpolymer beads are cooled and discharged
5 from the vessel substantially unexpanded. The beads are then expanded and molded by an expanded polystyrene bead molding process within the skill in the art. Such a process of making such polyethylene/polystyrene interpolymer beads is described for instance in U.S. Pat. No. 4,168,353.

A variation of the foregoing extrusion process readily yields expandable
10 thermoplastic polymer beads. The method tracks with the conventional foam extrusion process described above up to the die orifice, which now contains one or multiple holes. The variation requires (a) cooling the foamable gel to a temperature below that at which foaming occurs, (b) extruding cooled gel through a die containing one or more orifices to form a corresponding number of essentially continuous expandable
15 thermoplastic strands, (c) optionally quenching the strands exiting the die orifice in a cold water bath; and (d) and pelletizing the expandable thermoplastic strands to form expandable thermoplastic beads. Alternatively, the strands are converted to foam beads by cutting the strands into pellets or granules at the die face and allowing the granules to expand.

20 The foam beads can also be prepared by preparing a mixture of the polymer blend compositions of the present invention, cross-linking agent, and chemical blowing agent in a suitable mixing device or extruder and form the mixture into pellets, and heat the pellets to cross-link and expand.

In another process for making cross-linked foam beads suitable for molding
25 into articles, the blends of this invention are melted and mixed with a physical blowing agent in a conventional foam extrusion apparatus to form an essentially continuous foam strand. The foam strand is granulated or pelletized to form foam beads. The foam beads are then cross-linked by radiation. The cross-linked foam beads may then be coalesced and molded to form various articles as described above for the other foam
30 bead process. Additional teachings to this process are seen in U.S. Patent No. 3,616,365 and C.P. Park, above publication, pp. 224-228.

The foam beads may then be molded by any means known in the art, such as charging the foam beads to the mold, compressing the mold to compress the beads, and heating the beads such as with steam to effect coalescing and welding of the beads to form the article. Optionally, the beads may be impregnated with air or other blowing agent at an elevated pressure and temperature prior to charging to the mold. Further, the beads may optionally be heated prior to charging. The foam beads are conveniently then molded to blocks or shaped articles by a suitable molding method known in the art. Some of the methods are taught in U.S. Pat. Nos. 3,504,068 and 3,953,558. Excellent teachings of the above processes and molding methods are seen in C.P. Park, supra, p. 191, pp. 197-198, and pp. 227-233, U. S. Patent Nos. 3,886,100, U. S. Patent Nos. 3,959,189, U. S. Patent Nos. 4,168,353 and U. S. Patent Nos. 4,429,059.

The present crosslinked foam structure may also be made into a continuous plank structure by an extrusion process utilizing a long-land die as described in GB 2,145,961A. In that process, the polymer, chemical blowing agent and cross-linking agent are mixed in an extruder, heating the mixture to let the polymer cross-link and the blowing agent to decompose in a long-land die; and shaping and conducting away from the foam structure through the die with the foam structure and the die contact lubricated by a proper lubrication material.

The present crosslinked foam structure may be made in bun stock form by two different processes. One process involves the use of a cross-linking agent and the other uses radiation.

The present crosslinked foam structure may be made in bun stock form by mixing the blends of this invention, a cross-linking agent, and a chemical blowing agent to form a slab, heating the mixture in a mold so the cross-linking agent can cross-link the polymer material and the blowing agent can decompose, and expanding by release of pressure in the mold. Optionally, the bun stock formed upon release of pressure may be re-heated to effect further expansion.

Foam may be made from cross-linked polymer sheet by either irradiating polymer sheet with high energy beam or by heating a polymer sheet containing chemical cross-linking agent. The cross-linked polymer sheet is cut into the desired shapes and impregnated with nitrogen in a higher pressure at a temperature above the

softening point of the polymer; releasing the pressure effects nucleation of bubbles and some expansion in the sheet. The sheet is re-heated at a lower pressure above the softening point, and the pressure is then released to allow foam expansion.

Blowing agents useful in making the foam structures of the present invention

5 include inorganic agents, organic blowing agents and chemical blowing agents. Suitable inorganic blowing agents include carbon dioxide, nitrogen, argon, water, air, sulfur hexafluoride (SF₆) and helium. Organic blowing agents include aliphatic hydrocarbons having 1-9 carbon atoms, aliphatic alcohols having 1-3 carbon atoms, and fully and partially halogenated aliphatic hydrocarbons having 1-4 carbon atoms.

10 Aliphatic hydrocarbons include methane, ethane, propane, n-butane, isobutane, n-pentane, isopentane, neopentane. Aliphatic alcohols include methanol, ethanol, n-propanol, and isopropanol. Fully and partially halogenated aliphatic hydrocarbons include fluorocarbons, chlorocarbons, and chlorofluorocarbons. Examples of fluorocarbons include methyl fluoride, perfluoromethane, ethyl fluoride, 1,1-

15 difluoroethane (HFC-152a), fluoroethane (HFC-161), 1,1,1-trifluoroethane (HFC-143a), 1,1,1,2-tetrafluoroethane (HFC-134a), 1,1,2,2-tetrafluoroethane (HFC-134), 1,1,1,3,3-pentafluoropropane, pentafluoroethane (HFC-125), difluoromethane (HFC-32), perfluoroethane, 2,2-difluoropropane, 1,1,1-trifluoropropane, perfluoropropane, dichloropropane, difluoropropane, perfluorobutane, perfluorocyclobutane. Partially

20 halogenated chlorocarbons and chlorofluorocarbons for use in this invention include methyl chloride, methylene chloride, ethyl chloride, 1,1,1-trichloroethane, 1,1-dichloro-1 fluoroethane (HCFC-141b), 1-chloro-1,1-difluoroethane (HCFC-142b), chlorodifluoromethane (HCFC-22), 1,1-dichloro-2,2,2-trifluoroethane (HCFC-123) and 1-chloro-1,2,2,2-tetrafluoroethane (HCFC-124). Fully halogenated

25 chlorofluorocarbons include trichloromonofluoromethane (CFC-11), dichlorodifluoromethane (CFC-12), trichlorotrifluoroethane (CFC-113), dichlorotetrafluoroethane (CFC-114), chloroheptafluoropropane, and dichlorohexafluoropropane. Chemical blowing agents include azodicarbonamide, azodiisobutyro-nitrile, barium azodicarboxylate, N,N'-dimethyl-N,N'-

30 dinitrosoterephthalamide, and benzenesulfonhydrazide, 4,4-oxybenzene sulfonyl semicarbazide, and p-toluene sulfonyl semicarbazide, trihydrazino triazine and

mixtures of citric acid and sodium bicarbonate such as the various products sold under the name HydrocerolTM (a product of Boehringer Ingelheim). Any of the foregoing blowing agents may be used singly or in combination with one or more other blowing agents. Preferred blowing agents include isobutane, carbon dioxide, HFC-152a, and
5 mixtures of the foregoing.

The amount of blowing agent incorporated into the polymer melt material to make a foam-forming polymer gel is from 0.05 to 5.0, preferably from 0.2 to 3.0, and most preferably from 0.5 to 2.5 gram moles per kilogram of polymer.

Foams are optionally perforated to enhance or accelerate gaseous permeation
10 exchange wherein blowing agent exits from the foam and air enters into the foam. The resulting perforated foams have defined therein a multiplicity of channels that are preferably free of direction with respect to the longitudinal extension of the foam. The channels extend from one foam surface at least partially through the foam, and sometimes completely through the foam from one external surface to another external
15 surface. The channels are advantageously present over substantially an entire exterior foam surface, preferably with uniform or substantially uniform spacing. Suitable spacing intervals may be up to and including 2.5 centimeters (cm), preferably up to and including 1.3 cm. The foams optionally employ a stability control agent of the type described above in combination with perforation to allow accelerated permeation or
20 release of blowing agent while maintaining a dimensionally stable foam. U.S. Patents Nos. 5,424,016, . U.S. Patents Nos. 5,585,058, WO 92/19439 and WO 97/22455, provide excellent information relative to perforation. If desired, the foams of this invention may be post-treated by any known means to increase foam open cell content. Such post-treatment methods include, without limit, mechanically compressing the
25 foam and expanding the foam by exposure to steam or hot air.

Foams of the present invention generally have a density less than 900, preferably less than 850, more preferably less than 800 kg/m³, and even more preferably from 5 to 700 kilograms per cubic meter (in accordance with ASTM D3575-93, Suffix W, Method B). The foams generally have an average cell size of from 0.001
30 to 10.0, preferably from 0.002 to 5.0, and more preferably 0.003 to about 3.0 millimeters as measured according to the procedures of ASTM D3576. The preferred

ranges of density and cell size should not be taken as limiting the scope of this invention.

Foams of the present invention preferably exhibit excellent dimensional stability. Preferred foams retain 80 or more percent of their initial volume when
5 measured one month after an initial volume measurement within 30 seconds after foam expansion. Volume is measured by any suitable method such as cubic displacement of water.

The foams of the present invention have an open cell content that ranges from 0 to 100 volume percent based on the total volume of foam, as measured according to
10 ASTM D2856-94, depending upon component selection and process condition variations. Foams with an open cell content of 30 vol percent or less generally fall in a class known as closed cell foams. Those known as open cell foams typically have an open cell content greater than 30, preferably greater than 40, and more preferably greater than 50 vol percent. The open cell content is desirably 100 vol percent or less,
15 preferably 95 vol percent or less, and more preferably 90 vol percent or less.

The foams generally have an Asker-C hardness of ≤ 80 , desirably ≤ 75 , and preferably ≤ 70 . Hardness measurements of the foams use an Asker C durometer for cellular rubber and yarn in accordance with ASTM D2240-97, using a 5 mm diameter spherical indenter.

If the foam is in the shape of a sheet or plank, it has a thickness that is generally
20 ≥ 0.5 mm, preferably ≥ 1 mm and a width that is generally ≥ 5 mm, preferably ≥ 10 mm. As used herein "thickness" of a foam plank or sheet refers to its smallest cross-sectional dimension (for example, as measured from one planar surface to an opposing planar surface). When the foam is present as a round or rod, it has a diameter that is
25 generally ≥ 5 mm, preferably ≥ 10 mm.

The foam has a drop-test optimum C-factor (ASTM-D1596) of ≤ 6 , desirably ≤ 5 , and preferably ≤ 4 .

The foams of the present invention may be used in any application where foams of comparable density and open or closed cell contents are used today. Such
30 applications include, without limit, cushion packaging (for example, corner blocks,

braces, saddles, pouches, bags, envelopes, overwraps, interleaving, encapsulation) of finished electronic goods such as computers, televisions, and kitchen appliances; packaging or protection of explosive materials or devices; material handling (trays, tote boxes, box liners, tote box inserts and dividers, shunt, stuffing, boards, parts spacers and parts separators); work station accessories (aprons, table and bench top covers, floor mats, seat cushions); automotive (headliners, impact absorption in bumpers or doors, carpet underlayment, sound insulation); flotation (for example, life jackets, vests and belts); sports and leisure (for example, gym mats and bodyboards); thermal insulation such as that used in building and construction); acoustical insulation (for example, for appliances and building and construction); gaskets, grommets, seals; sound attenuation for printers and typewriters; display case insert; missile container padding; military shell holder; blocking and bracing of various items in transport; preservation and packaging; automotives anti-rattle pads, seals; medical devices, skin contact pads; cushioned pallet; and vibration isolation pad. The foregoing list merely illustrates a number of suitable applications. Skilled artisans can readily envision additional applications without departing from the scope or spirit of the present invention.

The film of the present invention may be a monolayer or a multilayer film. One or more layers of the film may be oriented or foamed. A multi-layer film of the present invention may contain one, two or more layers comprising a blend as defined herein. Preferably, the film according to the invention has a thickness of 0.5 to 10 mils. Preferably, the present invention pertains to a tough and stiff film, comprising the grafted blends of this invention. The film of the invention may be printed. The film of the invention is obtainable according to methods known in the art. The film may be made using a blown or a cast film extrusion process, including co-extrusion and extrusion coating. One or more layers of the film may be expanded, for example with a conventional blowing agent, to make foamed film. One or more films may be laminated to form a multi-layer structure. The films may be (further) oriented after forming via tenter frame, double-bubble or other blown film techniques.

In one embodiment, the film of the present invention is an oriented film. The term "orientation" as used herein refers to a process of stretching a hot polymeric

article to align the molecular chains in the direction(s) of stretching. When the stretching is applied in one direction, the process is called uniaxial orientation; when the stretching is applied in two (perpendicular) directions, the process is called biaxial orientation. Orientation can be uniaxial or, preferably, biaxial. Orientation may be accomplished according to conventional methods, such as blown film processes, “double-bubble” film processes, cast/tentered film processes or other techniques known in the art to provide orientation. The oriented films of the invention are particularly suitable for use in window envelope and related applications.

In another aspect, the present invention relates to a foamed film. Such film is especially suitable for use as label or in thermoformable articles of manufacture. To make foamed film structures, either physical or chemical blowing agents may be used. A multilayer film of the invention comprising one or more foamed layers comprising the grafted blends as defined herein is obtainable according to methods known in the art, for example, using a co-extrusion process. Preferred are two-layer or three-layer films with one or two surface layers and the foamed layer being the core layer. The surface layers may or may not comprise the grafted blends of this invention. In a three layer structure, preferably, the foamed layer is the core or middle layer.

The label film may be constructed from printed, slit to width, rolls of film with the labels glued to a container, for example a bottle, using conventional adhesives and glues known to the industry. In addition, the films of this invention may be printed, coated with pressure sensitive adhesives, laminated to release papers or films and applied to bottles, containers or other surfaces by conventional pressure sensitive techniques. The bottle may be a glass bottle or a PET bottle. Covering or affixed to a glass bottle, the label may also serve a protective purpose. If the bottle is a PET bottle, the preferred label is a wrap-around label.

The following examples illustrate, but do not in any way limit the scope of the present invention.

TEST METHODS

Melt Index was determined by ASTM D-1238 (190°C/2160g).

Resin (polymer) density was determined by ASTM D-792, employing Archimede's buoyancy displacement principal.

Flexural Modulus, 1 percent Secant Modulus and 2 percent Secant Modulus were measured in accordance with ASTM D-790, Method 1. The 1 percent Secant Modulus, 2 percent Secant Modulus and the Flex Modulus were determined using a bar of rectangular cross-section tested using a three-point loading system and a 10 pound load cell.

Melt Tension – The melt tension (in grams) was measured at 160°C and 190°C using a 2.16 kg load and pulling the strands of molten polymers at 50 rpm around a pulley system for a haul-off rate over a thirty second period. The melt tension was this average force.

Melt Strength - The measurements were conducted by pulling strands of molten polymers at constant acceleration until draw resonance or breakage occurred. The experimental set-up consisted of a capillary rheometer and a Rheotens apparatus as take-up device. The force required to uniaxially extend the strands was recorded as a function of the take-up velocity. The maximum force attained before significant draw resonance or breakage occurred was defined as the melt strength. The velocity at which draw resonance or breakage occurred was defined as the melt elongation. The tests were run under the following conditions :

Mass flow rate :	1.35 gram/minute
Temperature :	190°C (unless other indicated),
Capillary length :	41.9 mm
Capillary diameter :	2.1 mm
Piston diameter :	9.54 mm
Piston velocity :	0.423 mm/s
Shear rate :	33.0 s ⁻¹
Draw-down distance (die exit to take-up wheels):	100 mm
Cooling conditions :	ambient air

Acceleration : 2.4 mm/s²

Upper Service Temperature - A thermomechanical analyzer (TMA) commercially available from Perkin Elmer Corporation under the trade designation model TMA 7 was used to measure the upper service temperature (UST). Probe force of 102g and heating rate of 5°C/min were used. Each test specimen was a disk with thickness of 3.3 mm and 7.8 mm diameter, prepared by compression molding at 205°C and air-cooling to room temperature. Temperature at the probe penetration of 1 mm was taken as the upper service temperature (UST).

The glass transition temperatures (T_g) and peak melting temperature (T_m) were determined by differential scanning calorimetry (DSC). Sample size was approximately 5 mg. The following procedure was used for the DSC measurements: the sample was placed in a sealed aluminum pan and heated rapidly from ambient temperature to 180°C (at a rate of 105°C per minute); kept at 180°C for three minutes to ensure complete melting; cooled at 10°C/min to about -60°C or 40°C below the expected T_g; kept at this temperature for three minutes for DSC stabilization; and heated to 150°C (in general, for ethylenic and alkenyl aromatic polymers) and 190°C (for polypropylenes) at a rate of 10°C/min. The peak crystallization temperature (T_c) was obtained from the cooling curve. The peak melting temperature (T_m) was obtained from the melting curve (second heat) and was the peak melting temperature. The glass transition temperature (T_g) was obtained using the half-height method from the second heat DSC curve.

Gel Content was determined by xylene extraction - ASTM D-2765 Procedure "A" to measure the degree of crosslinking of polyethylene. Samples were immersed in xylene to extract what was not a gel (or crosslinked). After extraction, the sample was then dried and weighed. The resulting data was converted to percent gel.

EXAMPLES

The following blend components were used in the Examples

LDPE 620I is a low density polyethylene available from The Dow Chemical Company
PROFAX PF814 and PROFAX SR256M are polypropylenes available from and
trademarks of Montell.

H704-04 and H700-12 are polypropylene homopolymers available from The Dow
5 Chemical Company

ESI 1 is a substantially random ethylene styrene interpolymers (ESI) having a styrene
content of 39 mol percent and a melt index, I₂, of 1.0 g/10 min.

ESI 2 is a substantially random ethylene styrene interpolymers (ESI) having a styrene
content of 10 mol percent and a melt index, I₂, of 1.0 g/10 min.

10 ESI 3 is a substantially random ethylene styrene interpolymers (ESI) having a styrene
content of 29 mol percent and a melt index, I₂, of 0.5 g/10 min.

ESI 4 is a substantially random ethylene styrene interpolymers (ESI) having a styrene
content of 39 mol percent and a melt index, I₂, of 1.0 g/10 min.

EG8200 refers to AFFINITY™ EG8200 available from and a trademark of The Dow
15 Chemical Company.

DOWLEX™ 2045A is a linear low density polyethylene available from and a trademark
of The Dow Chemical Company.

STYRON™ 663 is a general purpose polystyrene available from and a trademark of The
Dow Chemical Company.

20 XU70262.08 refers to general purpose polystyrene of 11 g/10 min melt flow rate and is
available from The Dow Chemical Company

HDPE 10462N, 05862N and DSV10305.00 are high density polyethylenes available from
The Dow Chemical Company

HFE-034 is a high density polyethylene available from Mobil Chemical Company

25 LDPE 662I is a low density polyethylene available from The Dow Chemical Company

LDPE XSS84812.06 is a low density polyethylene of 0.923 g/cm³ density and 0.9 dg/min
melt index (I₂) available from The Dow Chemical Company

LDPE XUS61528.29 is a linear low density polyethylene of 0.919 g/cm³ density and 0.5
dg/min melt index (I₂) available from The Dow Chemical Company.

EST's 1 - 4 were prepared using the coatalysts, cocatalysts and polymerizations procedures as described in U.S. Patent No. 6,133,333, columns 14 - 23 and U.S. Patent No. 6,136,923, columns 14 - 19.

Embodiment 1

5 **Examples 1 - 24**

Different polymers were dry blended with various loadings of 4, 4'-oxybis(benzene sulfonyl azide) using 4000 ppm mineral oil as a tackifying agent. The blends were compounded on a Leistritz 18mm twin screw extruder with L/D = 30 at 200 rpm. Temperature settings were: Zone 1 – 130°C; zone 2 – 170°C; zone 3 – 190°C; zone 10 4 – 190°C; zone 5 – 190°C; die - 190°C. Final melt temperatures ranged from 205°C to 212°C. The same polymer blends were compounded without the azide (but with 4000 ppm mineral oil) under the same conditions for comparison.

The data are presented in Table 1. In general, the grafted blends exhibited improvements (increases) over the same blends without grafting in at least one of the 15 following :hardness, melt strength and/ upper service temperature . These data indicate that branching has been introduced by grafting of the various polymers.

Table 1

Ex #	Wt percent/Wt percent Component A & B	Azide (phr)	percent Gels	Hardness Shore A	Melt Strength and Melt Elongation at Indicated Temperatures			TMA - Temperature (°C) Corresponding to Various Probe Penetrations		
					(cN)	(mm/s)	Temp (°C)	0.1mm	0.2mm	1mm
Comp. Ex. 1	50/50 LDPE 620I & ESI 1	0	0.09	88.5	27	88	140	95.5	101.3	109.6
Ex. 1	50/50 LDPE 620I & ESI 1	0.1	0.108	87	31	67	140	104	107	111.5
Ex. 2	50/50 LDPE 620I & ESI 1	0.2	26.07	89	44	38	140	105.5	107.8	112.3
Comp. Ex. 2	30/70 LDPE 620I & ESI 1	0	0.15	78.5	23	158	150	53	60.5	80
Ex. 3	30/70 LDPE 620I & ESI 1	0.05	0.98	79	19	124	190	59.4	67.2	89.4
Ex. 4	30/70 LDPE 620I & ESI 1	0.1	1.29	78.5	32	54	150	87	95.5	109
Ex. 5	30/70 LDPE 620I & ESI 1	0.2	30.07	81.5	50	36	150	86.5	92	104.3
Ex. 6	30/70 LDPE 620I & ESI 2	0.1	0.62	84.5	N/A	N/A	N/A	63.1	68	78.3
Comp. Ex. 3	50/50 LDPE 620I & EG8200	0	1.24	81.5	13	180	140	86.5	92	104.2
Ex. 7	50/50 LDPE 620I & EG8200	0.1	1.13	82.5	30	55	140	95.5	99.1	107
Ex. 8	50/50 LDPE 620I & EG8200	0.2	5.9	82.5	45	32	140	96.6	101.4	107.5
Comp. Ex. 4	30/70 LDPE 620I & EG8200	0	1.28	75.5	6	160	140	60	64.1	75.1
Ex. 9	30/70 LDPE 620I & EG8200	0.05	1.09	77	5	390	190	65.4	68.7	80.2
Ex. 10	30/70 LDPE 620I & EG8200	0.1	1.50	77	21	60	140	70	76	95
Ex. 11	30/70 LDPE 620I & EG8200	0.2	2.31	78.5	33	52	140	67.5	73.4	93
Comp. Ex. 5	50/50 PROFAX PF814 & ESI 1	0	0.86	95	22	125	180	144	146	151
Ex. 12	50/50 PROFAX PF814 & ESI 1	0.1	1.08	96.5	40	23	180	145	147	153
Ex. 13	50/50 PROFAX PF814 & ESI 1	0.2	29.50	96	39	28	180	148	150	154.8
Comp. Ex. 6	50/50 PROFAX SR256M & ESI 1	0	1.25	90	4	130	180	132.5	135	142
Ex. 14	50/50 PROFAX SR256M & ESI 1	0.1	0.08	90.5	62	26	180	132	134.2	141.8
Ex. 15	50/50 PROFAX SR256M & ESI 1	0.2	41.86	90.5	60	23	180	132	135	144

Table 1 cont.

Comp Ex 7	30/70	PROFAX PF814 & ESI 1	0	0.60	88.5	19	137	190	66	75	100.5
Ex. 16	30/70	PROFAX PF814 & ESI 1	0.05	1.13	89	30	54	190	102.4	111	132.9
Ex. 17	30/70	PROFAX PF814 & ESI 1	0.1	0.46	89.5	37	27	190	112	126	145.5
Ex. 18	30/70	PROFAX PF814 & ESI 1	0.2	19.71	89.5	34	26	190	135	140	150
Ex. 19	30/70	H704-04 & ESI 1	0.025	1.07	90	12	90	190	68.7	76.1	95.6
Ex. 20	30/70	H704-04 & ESI 1	0.05	0.62	90.5	24	50	190	77.6	88.8	121.6
Ex. 21	30/70	H704-04 & ESI 2	0.05	0.51	91	39	33	190	67.7	71.6	86.5
Ex. 22	30/70	H704-04 & ESI 2	0.1	0.75	93.5	N/A	N/A	N/A	74.1	78.8	119.2
Ex. 23	30/70	H704-04 & ESI 2	0.15	1.14	93	N/A	N/A	N/A	78.7	87.9	133.5
Ex. 24	70/30	H704-04 & ESI 2	0.1	1.64	85.5	N/A	N/A	N/A	154.3	155.7	160.3

Examples 25 - 33

Different polymers were dry blended with various loadings of 4, 4'-oxybis(benzene sulfonyl azide) using 4000 ppm mineral oil as a tackifying agent. The blends were compounded on a Leistritz 18mm twin screw extruder with L/D = 30 at 200 rpm. Temperature settings were : Zone 1 – 130°C; zone 2 – 170°C; zone 3 – 190°C; zone 4 – 190°C; zone 5 – 190°C; die - 190°C. Final melt temperatures ranged from 183°C to 212°C. The same polymer blends were compounded without the azide (but with 4000 ppm mineral oil) under the same conditions for comparison. In general, the extruder exit pressure, extruder torque, hardness, melt strength and upper service temperature increased with increasing amounts of the azide. These data in Table 2 indicate that branching had been introduced by coupling or grafting of the various polymers.

Table 2

Ex #	Blend Composition	0 ppm azide*	250 ppm azide	500 ppm azide	1000 ppm azide	2000 ppm azide
Ex 25	30/70 STYRON* 663/ESI 3					
	Melt Temperature (°C)	210	222	223	211	211
	Extruder exit pressure (psi)	700	850	930	900	1500
	Torque (m-g)	5500	5800	6000	6000	6500
	percent Gels	0.46	1.69	1.85	1.00	22.14
	Shore A hardness	78			82	89
	Melt strength (cN) at 170°C	N/A			89	109
	Melt elongation (mm/s) at 170°C	N/A			46	31
	Temp. to penetrate 0.1 mm in TMA (°C)	42	58.5	78.7	73	94
	Temp. to penetrate 0.2 mm in TMA (°C)	49	67.5	87.7	84	99.5
	Temp. to penetrate 1 mm in TMA (°C)	68	95.4	105.8	106	109
Ex. 26	30/70 STYRON* 663/ ESI 1					
	Melt Temperature (°C)	210	227	224	211	210
	Extruder exit pressure (psi)	650	560	675	950	1200
	Torque (m-g)	5900	4600	4800	6000	6100
	percent Gels	0.41	1.99	0.94	4.64	34.34
	Shore A hardness	90			90.5	93
	Melt strength (cN) at 170°C	37			95	99
	Melt elongation (mm/s) at 170°C	580			95	32
	Temp. to penetrate 0.1 mm in TMA (°C)	96	74	75.2	96	99.5
	Temp. to penetrate 0.2 mm in TMA (°C)	100	80.8	83.5	100	102.2
	Temp. to penetrate 1 mm in TMA (°C)	107	97.6	102	107	109
Ex 27	30/70 STYRON* 663/EG8200					
	Melt Temperature (°C)		217	213		
	Extruder exit pressure (psi)		400	500		
	Torque (m-g)		2000	2400		
	percent Gels		0.56	0.88		
	Shore A hardness					
	Temp. to penetrate 0.1 mm in TMA (°C)		60.4	61.7		
	Temp. to penetrate 0.2 mm in TMA (°C)		67.7	67.5		
	Temp. to penetrate 1 mm in TMA (°C)		75.4	75.3		

Table 2 cont.

Ex 28	30/70 XU70262.08/ ESI 3				
	Melt Temperature (°C)		227	227	
	Extruder exit pressure (psi)		675	700	
	Torque (m-g)		5200	5000	
	percent Gels		0.26	0.87	
	Shore A hardness				
	Temp. to penetrate 0.1 mm in TMA (°C)		56	80.7	
	Temp. to penetrate 0.2 mm in TMA (°C)		63.4	89	
	Temp. to penetrate 1 mm in TMA (°C)		84	103.8	
Ex. 29	50/50 STYRON* 663/ ESI 1				
	Melt Temperature (°C)	208		210	210
	Extruder exit pressure (psi)	650		600	1200
	Torque (m-g)	5800		5600	6200
	percent Gels	0.48		0.11	36.75
	Shore A hardness	94.5		94.5	94
	Melt strength (cN) at 170°C	60		128	98
	Melt elongation (mm/s) at 170°C	525		48	23
	Temp. to penetrate 0.1 mm in TMA (°C)	104.6		105.6	105.6
	Temp. to penetrate 1 mm in TMA (°C)	111		112	113
Ex. 30	50/50 STYRON* 663/ ESI 3				
	Melt Temperature (°C)	210		209	211
	Extruder exit pressure (psi)	710		850	1400
	Torque (m-g)	5800		5500	6400
	percent Gels	0.12		0.60	38.19
	Shore A hardness	94		93.5	95.5
	Melt strength (cN) at 190°C	26		50	68
	Melt elongation (mm/s) at 190°C	700		80	24
	Temp. to penetrate 0.1 mm in TMA (°C)	106		105	105.8
	Temp. to penetrate 1 mm in TMA (°C)	112		113	113
Ex. 31	50/50 STYRON* XU70262.08/ESI 3				
	Melt Temperature (°C)	210		212	195
	Extruder exit pressure (psi)	1000		750	1200
	Torque (m-g)	6500		5800	6800
	percent Gels	2.71		0.06	30.18
	Shore A hardness	94.5		95	96.5
	Melt strength (cN) at 190°C	12		38	90
	Melt elongation (mm/s) at 190°C	440		77	33
	Temp. to penetrate 0.1 mm in TMA (°C)	103		104	104
	Temp. to penetrate 1 mm in TMA (°C)	110		111	112
Ex 32	50/50 STYRON* XU70262.08/ ESI 1				
	Melt Temperature (°C)	205		183	206
	Extruder exit pressure (psi)	500		750	1150
	Torque (m-g)	5800		5900	6300
	percent Gels	0.95		1.36	42.99
	Shore A hardness	94		94.5	96.5
	Melt strength (cN) at 190°C	11		35	N/A
	Melt elongation (mm/s) at 190°C	180		190	N/A
	Temp. to penetrate 0.1 mm in TMA (°C)	103		103	102
	Temp. to penetrate 1 mm in TMA (°C)	109		110	111
Ex 33	50/50 STYRON* 663/EG8200				
	Melt Temperature (°C)	210		209	209
	Extruder exit pressure (psi)	500		700	750
	Torque (m-g)	5000		5200	5500
	percent Gels	1.00		12.52	40.98
	Shore A hardness	94.5		95	95.5
	Melt strength (cN) at 140°C	N/A		65	25
	Melt elongation (mm/s) at 140°C	N/A		33	48
	Temp. to penetrate 0.1 mm in TMA (°C)	99		104.6	104

* Not an Example of Claimed Invention.

Examples 34 - 36

Mixtures of linear low density polyethylene (LLDPE) and polystyrene (PS), or mixtures of low density polyethylene (LDPE) and PS, were dry blended with 4, 4'-oxybis(benzene sulfonyl azide) using 4000 ppm mineral oil as a tackifying agent. The blends were compounded on a Leistritz 18mm twin screw extruder with L/D = 30 at 125 rpm. Temperature settings were: Zone 1 -150°C; zone 2 -175°C; zone 3 -200°C; zone 4 -225°C; zone 5 -225°C; die -225°C. The comparative example was a film grade LLDPE that was run with 4000 ppm mineral oil at the same process settings. The data are presented in Table 3. In general, the grafted blends exhibited comparatively higher melt strength, improved melt elongation and very low gel content.

Table 3

	Comp. Ex 8	Ex 34	Ex 35	Ex 36
LLDPE XUS61528.29 (weight percent)	100		80	50
LDPE 662I (weight percent)		20		
PS XU70262.08 (weight percent)		80	20	50
Bisulfonyl azide (ppm)		500	500	500
Drakeol 34 mineral oil (ppm)	4000	4000	4000	4000
torque m-g	5500	2400	4700	3600
melt temp (°C)	240	233	233	234
die pressure (psi)	750	200	600	375
melt index (g/10min)	0.5	1.1	0.22	0.48
Melt strength (cN) at 190°C	6	26	18	21
Melt elongation (mm/s) at 190°C	120	315	300	400
Gel Content (percent)			0.926	

Examples 35 - 36

Mixtures of linear low density polyethylene (LLDPE) and polystyrene (PS) were dry blended with 4, 4'-oxybis(benzene sulfonyl azide) using 4000 ppm mineral oil as a tackifying agent. The blends were compounded on a 30 mm twin screw extruder at 100 rpm. Temperature settings were: Zone 1 -140°C; zone 2 -175°C; zone 3 -200°C; zone 4 -215°C; zone 5 -220°C; die -225°C. The comparative example was a film grade LLDPE that was run with 4000 ppm mineral oil at the same process settings. The data are presented in Table 4. The grafted blends exhibited comparatively higher melt strength and improved melt elongation.

Table 4

Blend Component	Comp. Ex 9	Ex 35	Ex 36
DOWLEX 2045A (weight percent)	100	80	20
PS XU70262.08 (weight percent)		20	80
Bisulfonyl azide (ppm)		300	750
Drakeol 34 mineral oil (ppm)	4000	4000	4000
Melt Temperature (°C)	243	243	243
Melt Index, I2 (dg/min)	N/A	0.67	0.64
Melt strength (cN) at 190°C	4	10	26
Melt elongation (mm/s) at 190°C	175	358	340
Gel Content (percent)	N/A	0.39	0.27
1 percent Secant Modulus (psi)		58135	297967
2 percent Secant Modulus (psi)		48894	280322
Flexural Modulus (psi)		70960	298835

Embodiment Two**5 Examples 37 - 39**

Mixtures of high density polyethylene (HDPE) and low density polyethylene (LDPE) were dry blended with 4, 4'-oxybis(benzene sulfonyl azide) using 4000 ppm mineral oil as a tackifying agent. The blends were compounded on a Leistritz 18mm twin screw extruder with $L/D = 30$ at 200 rpm. Temperature settings were: Zone 1 –130°C; zone 2 –170°C; zone 10 3 –190°C; zone 4 –190°C; zone 5 –190°C; die –190°C. The comparative examples were the individual polymers, or blends thereof, that were run with or without azide and with or without mineral oil at the same process settings. The data are presented in Table 5. In general, the grafted blends exhibited comparatively higher melt strength or melt tension and acceptable melt elongation (> 25 mm/s)

15

Table 5

	Wt percent / Wt percent Component A & B	Bisulfonfyl Azide	Mineral Oil	Density	Melt Index, I ₂	1 percent secant Modulus	2 percent secant Modulus	Flexural Modulus	Melt Tension 190°C	Melt Tension 160°C	Melt Strength At 190°C	Melt Elongation At 190°C	Melt Strength 160°C	Melt Elongation 160°C
		(phr)	(wt percent)	(g/cc)	(g/10min.)	psi (kPa)	psi (kPa)	psi (kPa)	(g)	(g)	(cN)	(mm/s)	(cN)	(mm/s)
Comp. Ex 10	20/80 662I & 10462N	0	0.40 percent	0.9539	4.923	168,162	138,889	195,144	3.64	5.87	7.7	400	10.5	335
Ex. 37	20/80 662I & 10462N	0.075	0.40 percent	0.9522	1.923				8.28	9.16	12.7	190	15	155
Ex. 38	20/80 662I & 10462N	0.1	0.40 percent	0.9519	1.307	144,491	118,883	171,186	N/A	N/A	13	115	13.5	125
Ex. 39	20/80 662I & 10462N	0.15	0.40 percent	0.9534	0.735				N/A	N/A	18	95	18	100
Comp. Ex 11	100 percent HDPE 10462N	0	0 percent	0.9645	8.606	227,445	190,411	248,627	0.52	0.47	0.7	380	0.9	340
Comp. Ex 12	100 percent HDPE 10462N	0	0.40 percent	0.9624	8.561	222,378	186,173	245,809	0.33	0.37	0.82	245	1	420
Comp. Ex 13	100 percent HDPE 10462N	0.1	0.40 percent	0.9612	2.849	197,204	165,783	220,950	3.78	3.9	N/A	175	4.5	290
Comp. Ex 14	100 percent HDPE 10462N	0.2	0.40 percent	0.9612	1.038				N/A	5.69	7.5	90	6.9	360
Comp. Ex 15	100 percent HDPE 05862N	0	0 percent	0.9633	5.162	210,393	176,554	232,033	0.75	0.79	1	385	1.5	410
Comp. Ex 16	100 percent HDPE DSV10305.00	0	0 percent	0.9550	1.114	161,016	132,346	192,315	2.22	2.34	4.2	175	6.5	335
Comp. Ex 17	100 percent HDPE HFE-034	0	0 percent	0.9495	2.317	169,417	141,752	195,794	1.75	2.66	3.2	145	4.2	325

Examples 40 - 43

A mixture of high density polyethylene (HDPE) and LDPE was dry blended with 4, 4'-oxybis(benzene sulfonyl azide) using mineral oil as a tackifying agent. The blend was compounded on a 40 mm twin screw extruder with at 252 rpm and 175 lb/hr. The temperature profile in the extruder was: Zone 2 -169°C; zone 3 -189°C; zone 4 -209°C; zone 5 -218°C; zone 6 -227°C; zone 7 -238°C; zone 8 -229°C; zone 9 -216°C; die -207°C. The final melt temperature was 285°C. The final properties of the blend are presented in Table 6.

Table 6

	Blend	I2 (g/10 min)	Density (g/cm ³)	Melt Strength (cN) at 190°C	Melt Elongation (mm/s) at 190°C
Example 40	20 percent wt percent LDPE 662I 80 wt percent HDPE 10462N - grafted with 0.075 phr Bisulfonylazide	0.80	0.9528	20	60

10

This blend was subsequently foamed using an extrusion foaming process with isobutane as blowing agent. The comparative example was a conventional foam made from LDPE 662I. The properties of the resulting foams are summarized in Table 7.

Table 7

	Polymer	Talc (phr)	GMS (phr)	Isobutane (phr)	Foam density (kg/m ³) - ASTM D3575- 93 Suffix W		Open Cells (vol percent) - ASTM D2856-87	3D average cell size (mm)	Hardness - 45 days ASTM D2240- 97
					Fresh	28 days			
Comp Ex 17	LDPE 662I	0.5	0.3	12	26.29	29.98	70.7	1.93	26.7
Ex 41	Grafted Blend of Example 40	0.5	0.3	10	33.34	34.30	42.5	2.31	38.7
Ex 42	Grafted Blend of Example 40	0.13	0.4	15	23.72	24.21	33.8	1.89	35.0
Ex 43	Grafted Blend of Example 40	0.13	0.4	20	19.24	20.84	26.9	1.89	36.3

15

Foams of density ranging from 19 kg/m³ to 34 kg/m³ were successfully made from grafted blends of HDPE and LDPE. Open cells could be varied from 27 to 43 vol percent. The cell sizes of the foams ranged from about 1.9 to 2.3 mm. The Asker C hardness of the foams made from grafted HDPE/LDPE blends was significantly

greater than that of the reference foam (Comparative Example 17), even at significantly lower foam density. These data indicate that foams made from grafted HDPE/LDPE blends would exhibit significantly higher load bearing capability relative to foams made from LDPE alone, at similar densities. Or, foams made from grafted HDPE/LDPE blends will have equivalent load bearing capability to LDPE foams, but at comparatively lower foam density.

Examples 44 - 45

A mixture of high density polyethylene (HDPE) and LDPE was dry blended with 4, 4'-oxybis(benzene sulfonyl azide) using 600 ppm mineral oil as a tackifying agent. The blend was compounded on a 40 mm twin screw extruder with at 278 rpm and 175 lb/hr. The temperature profile in the extruder was: Zone 2 –176°C; zone 3 –200°C; zone 4 –218°C; zone 5 –232°C; zone 6 –240°C; zone 7 –250°C; zone 8 –255°C; zone 9 –256°C; die –254°C. The final melt temperature was 268°C. The final properties of the blend are presented in Table 8.

Table 8

	Blend	I2 (g/10 min)	Density (g/cm ³)	Melt Strength (cN) at 190°C	Melt Elongation (mm/s) at 190°C
Ex 44	20 percent wt percent LDPE 662I 80 wt percent HDPE 10462N 0.1 phr Bisulfonylazide	0.85	0.9532	16	89

This blend was subsequently foamed using an extrusion foaming process with isobutane as blowing agent. The comparative example was a conventional foam made from LDPE 620I. The foams were about 38 mm thick. Some of the foams were subsequently perforated (using needles of about 2 mm diameter spaced about 10 mm apart) completely in the vertical/thickness direction and aged at room temperature for at least 7 days before testing foam properties, except open cell contents which were measured on non-perforated foams. The properties of the foams are summarized in Table 9.

Table 9

Test Property	Test Method	Units	direction	Comp Ex 18	Ex 45
				Foam from LDPE 620I	Foam from Ex 44
Cell Size		mm	vertical	2.03	1.82
			extrusion	1.41	1.55
			horizontal	1.64	1.71
			average	1.69	1.69
Compression Creep	ASTM D3575-93 Suffix BB	percent Linear Change	vertical	22.0	23.1
Compression Deflection	ASTM D3575-93 Suffix D	kPa			
5 percent compression			vertical	17.9	13.7
			extrusion	33.6	50.2
			horizontal	14.4	15.0
10 percent compression			vertical	25.9	26.3
			extrusion	48.6	74.2
			horizontal	20.6	23.5
25 percent compression			vertical	42.2	51.3
			extrusion	62.7	88.5
			horizontal	34.8	40.4
50 percent compression			vertical	91.8	100.7
			extrusion	117.7	138.6
			horizontal	83.9	87.3
75 percent compression			vertical	255.7	257.7
			extrusion	342.2	345.1
			horizontal	245.8	246.1
Compression Set at 50 percent compression	ASTM D3575-93 Suffix B	percent Linear Change	vertical	21.7	23.6
Density		kg/m ³		25.31	33.64
Open Cell	ASTM D2856-94	Volume percent		6.84	50.70
Thermal Stability 110°C	ASTM D3575-93 Suffix S	percent Linear Change	extrusion	-9.9	-2.2
			horizontal	-7.7	3.3
			vertical	-2.5	6.7

The thermal stability data indicate that foams made from the grafted HDPE/LDPE blend exhibited better dimensional stability at 110°C than the foam of comparative example 18.

Examples 46 – 55

A series of grafted blends were prepared from HDPE and LDPE using a Leistritz 18mm twin screw extruder with L/D = 30 at 100 rpm. Temperature settings were: Zone 1 –150°C; zone 2 –175°C; zone 3 –200°C; zone 4 –225°C; zone 5 –225°C; die – 225°C. Final melt temperatures ranged from 237°C to 244°C. The comparative examples were the blends that were run without grafting agent and

without mineral oil at the same process settings. The grafting agents used were with 4, 4'-oxybis(benzene sulfonyl azide) and Lupersol™ 130 (2,5-dimethyl-2,5-di-(t-butylperoxy) hexyne-3), the latter a trademark and product of Elf Atochem.

The data, summarized in Table 10, indicate that grafted blends HDPE/LDPE exhibit increased melt strength and a melt elongation greater than 25 mm/s enabling subsequent fabrication of the improved articles of the present invention.

Table 10

Example	wt percent / wt percent Component A & Component B & Component C	Mineral Oil (percent)	Bisulfonyl Azide (phr)	Lupersol 130 (phr)	Density (g/cm ³)	Gel Content (percent)	Melt Strength (cN) 190°C	Melt Elongation (mm/s) 190°C
Comp Ex 19	80/20 HDPE 10462N & LDPE 662I	0	0	0	0.9538	0.470	6	350
Comp Ex 20	85/15 HDPE DSV10305.00 & LDPE 620I	0	0	0	0.9505	0.460	8	200
Ex. 46	80/20 HDPE 10462N & LDPE 662I	0.4	0.05	0	0.9528	0.343	7.5	200
Ex. 47	80/20 HDPE 10462N & LDPE 662I	0.4	0.1	0	0.9526	0.292	9	140
Ex. 48	79.4/20/0.6 HDPE 10462N & LDPE 662I & EG8200	0	0.05	0	0.9532	0.436	7.5	175
Ex. 49	78.8/20/1.2 HDPE 10462N & LDPE 662I & EG8200	0	0.1	0	0.9519	0.582	9	155
Ex. 50	78.1/20/1.9 HDPE 10462N & LDPE 662I & EG8200	0	0.15	0	0.9511	0.382	11	67
Ex. 51	77.5/20/2.5 HDPE 10462N & LDPE 662I & EG8200	0	0.2	0	0.9513	0.169	13	57
Ex. 52	74.7/25/0.3 HDPE DSV10305.00 & LDPE 620I & EG8200	0	0.025	0	0.9468	0.310	22	43
Ex. 53	74.4/25/0.6 HDPE DSV10305.00 & LDPE 620I & EG8200	0	0.05	0	0.9457	0.410	27	38
Ex. 54	80/20 HDPE 10462N & LDPE 662I	0	0	0.1	0.9489	0.680	24	57
Ex. 55	85/15 HDPE DSV10305.00 & LDPE 620I	0	0	0.1	0.9478	0.510	46	36

Examples 56 - 61

A series of grafted blends similar in polymer composition to Examples 46 and 47 were made using a Leistritz 18mm twin screw extruder with L/D = 30 at 125 rpm. Temperature settings were: Zone 1 –150°C; zone 2 –175°C; zone 3 –200°C; zone 4 –225°C; zone 5 –225°C; die –225°C. The comparative example was LLDPE that was

run without grafting agent at the same process settings. The data are summarized in Table 11.

The grafted blends of Examples 56-58 exhibited higher melt strength and elongation than Comparative Example 21, at relatively higher melt index. That is, the grafted blends of Examples 56-58 would exhibit better processability in applications requiring high melt strength. Additionally, the modulus and upper service temperature of the grafted blends of Examples 56-58 would be significantly greater than that of the LLDPE resin.

The grafted blends of Examples 59-61 exhibited even higher melt strength, with acceptable melt elongation, at very low melt index. The gel content was still very low.

Table 11

	Comp Ex 21	Ex 56	Ex 57	Ex 58	Ex 59	Ex 60	Ex 61
LLDPE XUS61528.29 (wt percent)	100						
HDPE 10462N (wt percent)		80	80	80	80	80	80
LDPE 662I (wt percent)		20	20	20	20	20	20
Bisulfonyl azide (ppm)		500	750	1000			
Lupersol 130 (ppm)					1000	1500	2000
Drakeol 34 mineral oil (ppm)	4000	4000	4000	4000	4000	4000	4000
torque m-g	5500	3600	3500	3600	6000	6700	7500
melt temp (°C)	240	235	236	239	239	240	241
die pressure (psi)	750	325	375	400	875	1100	1350
Nominal density (g/cm ³)	0.919	0.953	0.953	0.953	0.953	0.953	0.953
melt index (g/10min)	0.5	2.71	1.97	1.47	0.07	0.01	0.01
Melt strength (cN) at 190°C	6		8	9	24	32	47
Melt elongation (mm/s) at 190°C	120		175	160	60	44	40
Gel Content (percent)				0.74			0.797

The data in Table 11 indicate that grafted blends HDPE/LDPE exhibit increased melt strength and a melt elongation greater than 25 mm/s enabling subsequent fabrication of the improved articles of the present invention.

Examples 62 - 65

A series of grafted blends were prepared from HDPE and LDPE using a 30 mm twin screw extruder at 100 rpm. Temperature settings were : Zone 1 -140°C; zone 2 -175°C; zone 3 -200°C; zone 4 -215°C; zone 5 -220°C; die-225°C. Comparisons were made with LDPE (Comparative Example 22) and HDPE (Comparative Example 23) of similar melt index. The data are summarized in Table 12.

The grafted blend of Example 62 exhibited significantly higher modulus than Comparative Example 22 of similar melt index (0.8 dg/min) and identical melt strength (12 cN).

The grafted blend of Example 65 exhibited significantly higher melt strength than Comparative Example 23 of similar melt index (1 dg/min) and density (0.953-0.955 g/cm³). That is, the grafted blends of this invention exhibit processability similar to branched resins (for example, LDPE) with modulus and upper service temperature similar to that of linear polyethylene.

Table 12

	Comp Ex 22	Comp Ex 23	Ex 62	Ex 63	Ex 64	Ex 65
LDPE XSS84812.06	100					
HDPE DSV10305.00 (wt percent)		100				
HDPE 10462N (wt percent)			80	80	80	80
LDPE 662I (wt percent)			20	20	20	
LDPE 620I						20
Bisulfonyl azide (ppm)	none	none	1000			
Lupersol 130 peroxide (ppm)	none	none		150	300	300
Drakeol 34 mineral oil (ppm)	none	none	4000	4000	4000	4000
Melt Temperature (°C)	N/A	N/A	243	242	243	241
Melt Index, I2 (dg/min)	0.83	1.09	0.82	1.71	0.64	1.04
Melt strength (cN) at 190°C	12	4.3	12	9	13	8
Melt elongation (mm/s) at 190°C	180	110	140	225	95	170
Gel Content (percent)	N/A	0.95	0.41	0.45	0.44	0.39
Density (g/cm ³)	0.9236	0.9547	0.9531	0.9523	0.9517	0.9529
1 percent Secant Modulus (psi)	54842	166823	136301	136360	129390	135065
2 percent Secant Modulus (psi)	47371	140395	117612	115239	109004	114069
Flexural Modulus (psi)	62903	195851	145518	154459	146327	154952

Example 66

The grafted blend of Example 44 was further blended with an ethylene styrene interpolymer (ESI 4) at a 70:30 wt percent ratio and subsequently foamed using an extrusion foaming process with isobutane as blowing agent. The comparative example was a conventional foam made from LDPE 620I. The foams were about 38 mm thick. Some of the foams were subsequently perforated (using needles of about 2 mm diameter spaced about 10 mm apart) completely in the vertical/thickness direction and aged at room temperature for at least 7 days before testing foam properties, except open cell contents which were measured on non-perforated foams. The properties of the foams are summarized in Table 13.

Table 13.

Test Property	Test Method	Units	Direction	Comp Ex 24	Ex 66
				Foam made from LDPE 620I	Foam Made from 70/30 Blend of Grafted Blend of Example 44& ESI 4
Cell Size		mm	Vertical	2.03	1.82
			Extrusion	1.41	1.41
			Horizontal	1.64	1.47
			Average	1.69	1.57
Compression Deflection	ASTM D3575-93 Suffix D	kPa			
5 percent compression			Vertical	17.9	14.3
			Extrusion	33.6	31.2
			Horizontal	14.4	13.6
10 percent compression			Vertical	25.9	21.2
			Extrusion	48.6	42.7
			Horizontal	20.6	18.8
25 percent compression			Vertical	42.2	35.5
			Extrusion	62.7	52.6
			Horizontal	34.8	28.1
50 percent compression			Vertical	91.8	71.0
			Extrusion	117.7	89.3
			Horizontal	83.9	59.5
75 percent compression			Vertical	255.7	183.7
			Extrusion	342.2	229.9
			Horizontal	245.8	165.9
Compression Set at 50 percent Compression	ASTM D3575-93 Suffix B	percent Linear Change	Vertical	21.7	18.4
Density		kg/m ³		25.31	25.47
Open Cells	ASTM D2856-94	Volume percent		6.84	40.62
Thermal Stability at 110°C	ASTM D3575-93 Suffix S	percent Linear Change	Extrusion	-9.9	-2.8
			Horizontal	-7.7	-3.1
			Vertical	-2.5	1.7

Blending ESI with a grafted HDPE/LDPE blend results in foams that exhibit lower compression set and better thermal stability (dimensional stability) at 110°C than the foam of comparative example 24.

Embodiment 3

5 Examples 67 - 69

Mixtures of linear low density polyethylene (LLDPE) and polypropylene (PP), or mixtures of low density polyethylene (LDPE) and PP, were dry blended with various loadings of 4, 4'-oxybis(benzene sulfonyl azide) using 4000 ppm mineral oil as a tackifying agent. The blends were compounded on a Leistritz 18mm twin screw
 10 extruder with L/D = 30 at 125 rpm. Temperature settings were: Zone 1 –150°C; zone 2 –175°C; zone 3 –200°C; zone 4 –225°C; zone 5 –225°C; die –225°C. The comparative example was a film grade LLDPE that was run with 4000 ppm mineral oil at the same process settings. The data are presented in Table 14. The grafted
 15 blends exhibited comparatively higher melt strength and acceptable melt elongation (> 25 mm/s). Furthermore, the grafted blends of Examples 67-68 are expected to exhibit relatively higher modulus and upper service temperature than Comparative Example 25 because of the polypropylene used.

Table 14

	Comp Ex 25	Ex 67	Ex 68	Ex 69
LLDPE XUS61528.29 (wt percent)	100	80	80	
LDPE 662I (wt percent)				80
PP H700-12 (wt percent)		20	20	20
Bisulfonyl azide (ppm)		250	500	500
Drakeol 34 mineral oil (ppm)	4000	4000	4000	4000
torque m-g	5500	4200	5000	3500
melt temp (°C)	240	231	241	237
die pressure (psi)	750	500	700	600
melt index (g/10min)	0.5	0.36	0.1	0.13
Melt strength (cN) at 190°C	6	10	23	40
Melt elongation (mm/s) at 190°C	120	100	58	38
Gel content (percent)			0.501	0.771

20

Example 70

A mixture of linear low density polyethylene (LLDPE) and polypropylene (PP) was dry blended with 4, 4'-oxybis(benzene sulfonyl azide) using 4000 ppm mineral oil as a tackifying agent. The blend was compounded on a 30 mm twin screw extruder at 100
 25 rpm. Temperature settings were: Zone 1 –140°C; zone 2 –175°C; zone 3 –200°C; zone 4

–215°C; zone 5 –220°C; die –225°C. The comparative example was a film grade LLDPE that was run with 4000 ppm mineral oil at the same process settings. The data are presented in Table 15. The grafted blends exhibited comparatively higher melt strength and acceptable melt elongation (> 25 mm/s).

5

Table 15

	Comp Ex 26	Ex 70
DOWLEX 2045A (wt percent)	100	80
PP H700-12 (wt percent)		20
Bisulfonfyl azide (ppm)		300
Drakeol 34 mineral oil (ppm)	4000	4000
Melt Temperature (°C)	243	240
Melt Index, I2 (dg/min)	N/A	0.59
Melt strength (cN) at 190°C	4	8
Melt elongation (mm/s) at 190°C	175	100
Gel Content (percent)	N/A	0.41
1 percent Secant Modulus (psi)		57495
2 percent Secant Modulus (psi)		50412
Flexural Modulus (psi)		64321

CLAIMS

1. A grafted blend composition comprising,

5 (A) one or more homopolymers or interpolymers with peak crystalline melting temperature (T_m) and/or or glass transition temperature (T_g by DSC) of 90°C or more;

(B) one or more homopolymers or interpolymers with peak crystalline melting temperature (T_m) and/or glass transition temperature (T_g by DSC) of 80°C or less; and

10 (C) at least one coupling agent;

and wherein

1) the upper service temperature of said grafted blend is greater than about 80°C;

15 2) the gel content of said grafted blend is 50 percent or less (as determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84);

3) said grafted blend composition exhibits at least one of the following improvements relative to the same blend in the absence of Component C;

20 (a) the melt strength is increased by 5 percent or more; and/or

(b) the upper service temperature is increased by 0.5°C or more.

2. The grafted blend composition of Claim 1 wherein

25 A) Component A is present in an amount of from 0.5 to 99.5 percent by weight (based on the combined weights of Components A, B and C);

B) Component B is present in an amount of from 0.5 to 99.5 percent by weight (based on the combined weights of Components A, B and C) and

30 C) Component C is one or more of poly (sulfonyl) azides and/or peroxides; and wherein

1) Components A and B are selected from the group consisting of the substantially random interpolymers, the olefinic

polymers; the alkenyl aromatic polymers, or any combination thereof;

- 2) the upper service temperature of said grafted blend is greater than about 85°C;
- 3) the gel content of said grafted blend is 40 percent or less (as determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84); and
- 4) said grafted blend composition exhibits at least one of the following improvements relative to the same blend in the absence of Component C;
 - (a) the melt strength is increased by 10 percent or more; and/or
 - (b) the upper service temperature is increased by 1.0°C or more.

3. The grafted blend composition of Claim 1 wherein

- A) Component A is present in an amount of from 5 to 95 percent by weight (based on the combined weights of Components A, B and C);
- B) Component B is present in an amount of from 5 to 95 percent by weight (based on the combined weights of Components A, B and C) and
- C) Component C is one or more of poly (sulfonyl) azides and/or peroxides; and wherein
 - 1) Components A and B are selected from the group consisting of an ethylene homopolymer or copolymer, a propylene homopolymer or copolymer, a styrene homopolymer or copolymer, a substantially random ethylene/styrene or ethylene/ α -olefin/styrene interpolymer or a combination thereof;
 - 2) the upper service temperature of said grafted blend is greater than about 90°C;

- 3) the gel content of said grafted blend is 30 percent or less (as determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84); and
- 5 4) said grafted blend composition exhibits at least one of the following improvements relative to the same blend in the absence of Component C;
- (a) the melt strength is increased by 10 percent or more; and/or
- (b) the upper service temperature is increased by
- 10 1.5°C or more.
4. The grafted blend composition of Claim 1 wherein
- A) Component A is present in an amount of from 10 to 90 percent by weight (based on the combined weights of Components A, B and
- 15 C);
- B) Component B is present in an amount of from 10 to 90 percent by weight (based on the combined weights of Components A, B and C) and
- C) Component C is one or more of poly (sulfonyl) azides and/or
- 20 peroxides; and wherein
- 1) Components A and B are selected from the group consisting of an ethylene homopolymer or copolymer, a propylene homopolymer or copolymer, a styrene homopolymer or copolymer, a substantially random ethylene/styrene or
- 25 ethylene/ α -olefin/styrene interpolymers or a combination thereof;
- 2) the upper service temperature of said grafted blend is greater than about 90°C;
- 3) the gel content of said grafted blend is 20 percent or less (as
- 30 determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84); and

said grafted blend composition exhibits at least one of the following improvements relative to the same blend in the absence of Component C;

(a) the melt strength is increased by 10 percent or more;
and/or

(b) the upper service temperature is increased by 1.5°C
or more relative to the same blend in the absence of
Component C.

5. The grafted blend composition of Claim 4 wherein

A) Component A is present in an amount of from 10 to 60 percent by
weight (based on the combined weights of Components A, B and C)
and

B) Component B is present in an amount of from 40 to 90 percent by
weight (based on the combined weights of Components A, B and C);
and

and wherein

a) the gel content of said grafted blend is 10 percent or less;
and

b) the upper service temperature of said grafted blend
composition is increased by 5°C or more relative to the
same blend in the absence of Component C.

6. A grafted blend composition comprising

(A) a blend of;

1) one or more linear or substantially linear ethylene homopolymers or
interpolymers and one or more branched ethylene homopolymers or
interpolymers;

2) one or more linear or substantially linear ethylene homopolymers or
interpolymers and one or more substantially random interpolymers; or

3) one or more linear or substantially linear ethylene homopolymers or
interpolymers, one or more branched ethylene homopolymers or interpolymers
and one or more substantially random interpolymers; and

(B) one or more coupling agents;

and wherein said grafted blend composition has

- a) a melt strength, greater than about 8cN;
- b) a melt elongation of 20 mm/s or greater;
- c) a flexural modulus of 80,000 psi or greater; and
- d) a gel content which is 50 percent or less, as determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84.

7. The grafted blend composition of Claim 6 wherein said grafted blend composition has

- a) a melt strength, greater than about 10 cN,
- b) a melt elongation of 25 mm/s or greater;
- c) a flexural modulus of 100,000 psi or greater; and
- d) a gel content which is 40 percent or less, as determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84.

8. The grafted blend composition of Claim 6 wherein said grafted blend composition has

- a) a melt strength, greater than about 15 cN,
- b) a melt elongation of 30 mm/s or greater;
- c) a flexural modulus of 110,000 psi or greater, and
- d) a gel content which is 30 percent or less, as determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84.

9. The grafted blend composition of Claim 8 wherein;

- A) said polymer blend Component (A) comprises a blend of HDPE with LDPE;
- B) and said coupling agent, Component (B) is on azide or a peroxide or a combination thereof.

10. The grafted blend composition of Claim 8 wherein;

A) said polymer blend Component (A) comprises a blend of heterogeneous or homogeneous LLDPE with LDPE; and

5 B) said coupling agent, Component (B) is an azide or a peroxide or a combination thereof.

11. The grafted blend composition of Claim 8; wherein

10 A) said polymer blend Component (A) comprises a blend of a substantially linear ethylene homopolymer or interpolymer with LDPE and said coupling agent; and

B) Component (B) is an azide or a peroxide or a combination thereof.

12. A grafted blend composition which has a melt index, I_2 , of 0.05 to 10 g/10 min comprising;

15 A) from 55 to 90 wt percent (based on the combined weights of component A and B) of a linear or substantially linear ethylene homopolymer or interpolymer, having a density of greater than 0.9450 g/cm³;

20 B) from 10 to 45 wt percent (based on the combined weights of component A and B) of a branched ethylene homopolymer or interpolymer having a melt strength of greater than 5 cN; and

C) from 0.005 wt percent to about 0.2 wt percent (based on the combined weights of A and B) of a coupling agent; and

25 D) wherein the melt strength of said grafted blend is greater than 5 cN.

13. A grafted blend composition comprising,

(A) one or more olefinic polymers other than polypropylene;

30 (B) one or more propylene homopolymers or interpolymers; and

(C) at least one coupling agent;

and wherein said grafted blend has

- 1) a gel content which is 50 percent or less, as determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84;
 - 2) a melt elongation greater than or equal to about 20 mm/s,
 - 5 3) a melt strength greater than about 5 cN; and
 - 4) a flexural modulus of 50,000 psi or greater.
14. The grafted blend composition of Claim 13 wherein;
- 10 1) said gel content is 40 percent or less, as determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84;
 - 2) said melt elongation is greater than or equal to about 25 mm/s;
 - 3) said melt strength is greater than about 10.
- 15 15. The grafted blend composition of Claim 13 comprising, wherein
- 1) said coupling agent is an azide or a peroxide or a combination thereof;
 - 2) said gel content is 30 percent or less as determined by insolubility of the gels in boiling xylene when tested according to ASTM D-2765A-84; and
 - 20 3) said melt strength is greater than about 15 cN.
16. A blend comprising from 0.1 to 99.9 wt percent of the grafted blend composition of claims 1, 6, and 13; and further comprising from 0.1 to 99.9 wt percent of a thermoplastic polymer.
- 25 17. A fabricated article comprising the grafted blend composition of Claims 1, 6, and 13 in the form of a film, fiber, blow molded article or extrusion coating.
- 30 18. A foam comprising the grafted blend composition of Claims 1, 6, and 13 and having a crosslinked gel content of 50 percent or less, and a density less than 900 kilograms per cubic meter.

19. The foam of Claim 18 having a crosslinked gel content of 30 percent or less, and a density less than 850 kilograms per cubic meter.
- 5 20. The foam of Claim 18 having a crosslinked gel content of 10 percent or less, and a density ranging from 5 to 700 kilograms per cubic meter.
21. The foam of Claim 18 having a crosslinked gel greater than 50 percent, and a density less than 900 kilograms per cubic meter.
- 10 22. The foam of Claim 18 having a crosslinked gel greater than 55 percent, and a density less than 850 kilograms per cubic meter.
23. The foam of Claim 18 having a crosslinked gel greater than 60 percent, and a density ranging from 5 to 700 kilograms per cubic meter.
- 15 24. The foam of Claims 18 to 23, wherein the foam has an open cell content of 30 volume percent or less.
25. The foam of Claims 18 to 23, wherein the foam has an open cell content of 20 volume percent or less.
- 20 26. The foam of Claims 18 to 23, wherein the foam has an open cell content of 10 volume percent or less.
- 25 27. The foam of Claims 18 to 23, wherein the foam has an open cell content of greater than 30 volume percent.
28. The foam of Claims 18 to 23, wherein the foam has an open cell content of greater than 40 volume percent.
- 30 29. The foam of Claim 18 to 23,, wherein the foam has an open cell content of greater than 50 volume percent.

30. The foam of Claim 18, wherein the foam has defined therein a multiplicity of channels, the channels being free of direction with respect to the longitudinal extension of the foam and enhancing or accelerating a gaseous permeation exchange wherein blowing agent exits from the foam and air enters into the foam.
31. The foam of Claim 18, wherein the foam is in the shape of a sheet or plank with a thickness of at least 0.5 millimeters and width of at least 5 millimeters, or a rod having a diameter of at least 5 millimeters.
32. The foam of Claim 18, wherein the foam is shaped as thermoplastic foam beads or as expanded and fused thermoplastic foam beads.
33. The foam of Claim 18, wherein the foam is a unitary foam structure that is a coalesced strand foam.
34. A process for making a polymer foam; which comprises;
- (i) converting the grafted blend composition of Claims 1, 6, and 13 into a polymer melt;
 - (ii) introducing, at an elevated pressure, at least one blowing agent into the polymer melt to form a foamable gel, the blowing agent being present in a total amount of from 0.05 to 5.0 gram-moles per kilogram of polymers contained in the polymer melt;
 - (iii) cooling the foamable gel to an optimum temperature; and
 - (iv) extruding the foamable gel from step iii through a die to a region of lower pressure to form a foam.
35. The process of claim 34, wherein said die is a multi-orifice die with orifice spacing sufficient to ensure that contact between surfaces of adjacent streams of extrudate occurs during foaming in the region of lower pressure, the contact being sufficient to ensure that the contacting surfaces adhere to one another

with sufficient adhesion to result in a unitary foam structure that is a coalesced strand foam.

- 5 36. The process of claim 34, wherein steps (iii) and (iv) constitute an intermittent process that employs an accumulating extruder means to first accumulate foamable gel in a holding zone maintained at a temperature and pressure which does not allow the gel to foam and then periodically eject accumulated gel through the die.
- 10 37. The process of claim 34, wherein the optimum temperature is a temperature at which foaming does not occur and step (iv) is modified such that no foaming occurs and the resulting extrudate is pelletized to form expandable thermoplastic beads.
- 15 38. A process for making a foam in the form of thermoplastic foam beads, which process comprises sequential steps (i) – (v);
- (i) converting the grafted blend composition of Claims 1, 6, and 13 into a polymer melt;
 - (ii) cooling and granulating the polymer melt to form discrete resin particles;
 - (iii) creating a suspension by dispersing the resin particles in a liquid medium in which they are substantially insoluble;
 - (iv) introducing, at an elevated temperature and pressure, at least one blowing agent (and optionally a cross-linking agent) into the suspension to form resin particles having a blowing agent incorporated therein; and
 - (v) rapidly discharging product formed in step iv into an atmosphere that promotes converting the product into foam beads.
- 20
- 25
- 30

39. A process for preparing grafted blend compositions comprising a coupling agent in solid form and a polymer or polymer blend composition, said process comprising;
- 5 1) mixing said polymer or polymer blend with a tackifier;
- 2) tumble blending the mixture from step 1 with said coupling agent; and
- 3) extruding the resulting mixture at a temperature at which the coupling agent is activated
- 10 40. A process for preparing grafted blend composition comprising a coupling agent in liquid form and a polymer or polymer blend composition, said process comprising;
- 1) mixing said coupling agent with a tackifier, and
- 2) tumble blending the mixture from step 1 with said polymer or
- 15 polymer blend composition; and
- 3) extruding the resulting mixture at a temperature at which the coupling agent is activated.
41. The process of Claims 39 and 40, wherein said tackifier is a mineral oil and is
- 20 present in an amount of from 0.2 to 2 percent by weight (based on the weight of the final grafted blend composition).
42. A process for preparing grafted blend composition comprising a coupling agent and resin comprising a polymer blend composition, said process
- 25 comprising;
- 1) preparing a mixture of the coupling agent; and a resin comprising one of the components of said polymer blend, and extruding the resulting mixture at a temperature at which the coupling agent is not activated;
- 30 2) adding the remaining component(s) of said polymer blend composition, other than that used in step (1), to the mixture from step (1), in an amount required to give the final desired

concentration of coupling agent (based on the weight of the final grafted blend composition); and

- 3) extruding the mixture from step 3 at a temperature at which the coupling agent is activated.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 June 2001 (07.06.2001)

PCT

(10) International Publication Number
WO 01/40374 A3

(51) International Patent Classification?: C08J 9/04, C08L 23/04, 23/10, C08K 5/43, C08F 8/34

(US). DELLAMEA, Jennifer [US/US]: 420 Garland Drive, Lake Jackson, TX 77566 (US).

(21) International Application Number: PCT/US00/32748

(74) Agent: SPENCER, Lee: Intellectual Property, B-1211, 2301 Brazosport Blvd., Freeport, TX 77541 (US).

(22) International Filing Date: 1 December 2000 (01.12.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/168,702 3 December 1999 (03.12.1999) US

(63) Related by continuation (CON) or continuation-in-part (CIP) to earlier application:
US 60/168,702 (CIP)
Filed on 3 December 1999 (03.12.1999)

(71) Applicant (for all designated States except US): THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Midland, MI 48674 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): CHAUDHARY, Bharat, I. [IN/US]; 3419 Woodbine Place, Pearland, TX 77584 (US). HO, Thoi, H. [US/US]; 54 Orchid Court, Lake Jackson, TX 77566 (US). OSWALD, Thomas, T. [CA/US]; 323 Huckleberry, Lake Jackson, TX 77566

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(88) Date of publication of the international search report:
28 February 2002

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: GRAFTED THERMOPLASTIC COMPOSITIONS AND FABRICATED ARTICLES THEREFROM

(57) Abstract: This invention describes grafted blend compositions, processes for their preparation and fabricated articles, especially foams therefrom. The blends exhibit enhanced melt strength, melt elongation greater than or equal to about 20 mm/s, increased upper service temperature, increased modulus, and increased hardness. The grafted blend compositions have little or no high shear viscosity increase over a corresponding polymer of the same chemical composition absent the coupling agent.

WO 01/40374 A3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/32748

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08J9/04 C08L23/04 C08L23/10 C08K5/43 C08F8/34

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08J C08L C08K C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	WO 00 52091 A (HO THOI H ; DOW CHEMICAL CO (US); DRUMRIGHT RAY E (US); TERBRUEGGEN) 8 September 2000 (2000-09-08) page 3, line 2; claims 1,5,6,11,12,19,24; table 3 page 9, line 20 - line 21 page 17, line 22 - page 18, line 21 page 22, line 30 - page 23, line 7 page 26, line 8 - page 29, line 19 page 33, line 10 - line 12 ---	1-5, 16-38, 42
X	WO 99 10426 A (MULLINS MICHAEL J ; HO THOI H (US); CUMMINS CLARK H (US); DOW CHEMI) 4 March 1999 (1999-03-04)	39-41
Y	page 1, line 34 - line 42; claims 1,2,9; examples 1,2; tables 3,4 page 23, line 9 - line 42 page 38, line 20 - line 24 ---	16-38
	-/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *8* document member of the same patent family

Date of the actual completion of the international search

13 September 2001

Date of mailing of the international search report

02.10.01

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Clemente Garcia, R

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/32748

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 883 145 A (HURLEY ROBERT F ET AL) 16 March 1999 (1999-03-16)	6-11,42
Y	column 1, line 42 - line 46 column 8, line 66 - column 9, line 6 column 10, line 56 - line 67; claims 1-4,13,22,23; example 7; table 1 ----	16-38
Y	WO 96 16119 A (BAKER SHARON L ;DOW CHEMICAL CO (US); JAIN PRADEEP (US); KALE LAWR) 30 May 1996 (1996-05-30) page 20, line 17 - line 20; claim 1 ----	12
Y	WO 99 10415 A (MULLINS MICHAEL J ;ROWLAND MICHAEL E (US); HO THOI H (US); KAO CHE) 4 March 1999 (1999-03-04) page 51, line 6 - line 27; example 8 page 53, line 4 - line 23; claims ----	12
X	US 5 929 129 A (FEICHTINGER KURT) 27 July 1999 (1999-07-27) column 1, line 20 - line 23; claims 1-16 column 12, line 22 - line 26 column 14, line 59 - line 61; examples VI,VII ----	13-15
A	GB 1 022 051 A (HERCULES POWDER CO LTD) 9 March 1966 (1966-03-09) page 3, column 42, line 50; example 44 page 12, line 24 - line 65; claims -----	13-15

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 00/32748

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☒ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☒ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. Claims: 1-5, 16-42 (claims 16-42 as related to claim 1)

Grafted blend of polymers having different Tg and a coupling agent, the blend is characterised by: upper service temperature >80°C and a gel content of <50%

2. Claims: 6-11,
16-42 (claims 16 to 42 as relating to claim 6)

Grafted blend of substantially linear ethylene polymers with a second polymer and a coupling agent, the blend being characterised by: melt strength >8cN, gel content <50% and specific values of melt elongation and flexural modulus.

3. Claims: 12, 39-42 (claims 39 to 42 as related to claim 12)

Grafted blend of substantially linear polyethylene with a branched polyethylene and a coupling agent the blend is characterised by: melt strength >5cN and specific melt index

4. Claims: 13-15,
16-42 (claims 16 to 42 as relating to claim 13))

Grafted blend comprising a polymer different from PP, a polypropylene polymer and a coupling agent, the blend being characterised by: melt strength >5cN, a gel content <50% and specific values of melt elongation and melt strength.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/32748

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0052091	A	08-09-2000	US 6277916 B1	21-08-2001
			AU 3608600 A	21-09-2000
			WO 0052091 A1	08-09-2000
WO 9910426	A	04-03-1999	AU 8782598 A	16-03-1999
			AU 8920898 A	16-03-1999
			BR 9814450 A	03-10-2000
			BR 9814451 A	03-10-2000
			CN 1275142 T	29-11-2000
			CN 1275996 T	06-12-2000
			EP 1007588 A1	14-06-2000
			EP 1007589 A1	14-06-2000
			HU 0002761 A2	28-12-2000
			NO 20000962 A	17-04-2000
			PL 338863 A1	20-11-2000
			TR 200000516 T2	22-01-2001
			WO 9910424 A1	04-03-1999
			WO 9910426 A1	04-03-1999
			AU 8688198 A	16-03-1999
			AU 8688298 A	16-03-1999
			AU 8688398 A	16-03-1999
			AU 8828398 A	16-03-1999
			AU 8921098 A	16-03-1999
			CN 1271371 T	25-10-2000
			CN 1273592 T	15-11-2000
			CN 1276811 T	13-12-2000
			EP 1007585 A1	14-06-2000
			EP 1007586 A1	14-06-2000
			EP 1007587 A1	14-06-2000
			EP 1007583 A1	14-06-2000
			EP 1007590 A1	14-06-2000
			HU 0002756 A2	28-12-2000
			NO 20000966 A	25-04-2000
			PL 339083 A1	04-12-2000
			TR 200000905 T2	21-07-2000
			TR 200001175 T2	21-08-2000
			WO 9910421 A1	04-03-1999
			WO 9910422 A1	04-03-1999
			WO 9910423 A1	04-03-1999
			WO 9910415 A1	04-03-1999
			WO 9910427 A1	04-03-1999
			US 6211302 B1	03-04-2001
			US 6143829 A	07-11-2000
US 5883145	A	16-03-1999	EP 0702032 A2	20-03-1996
			JP 8176332 A	09-07-1996
			US 6103775 A	15-08-2000
			US 5932659 A	03-08-1999
			US 5929129 A	27-07-1999
			US 5883144 A	16-03-1999
WO 9616119	A	30-05-1996	US 5582923 A	10-12-1996
			AT 185829 T	15-11-1999
			AU 691386 B2	14-05-1998
			AU 4283096 A	17-06-1996
			BR 9510328 A	02-06-1998
			CA 2205116 A1	30-05-1996
			DE 69512932 D1	25-11-1999

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/32748

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9616119	A	DE 69512932 T2	09-03-2000
		EP 0792318 A1	03-09-1997
		ES 2137558 T3	16-12-1999
		FI 972032 A	11-07-1997
		JP 10509200 T	08-09-1998
		NO 972203 A	14-07-1997
		WO 9616119 A1	30-05-1996
		ZA 9509615 A	13-05-1997
		US 5773155 A	30-06-1998
		US 5863665 A	26-01-1999
WO 9910415	A	04-03-1999	
		AU 8688198 A	16-03-1999
		AU 8688298 A	16-03-1999
		AU 8688398 A	16-03-1999
		AU 8828398 A	16-03-1999
		AU 8920898 A	16-03-1999
		AU 8921098 A	16-03-1999
		BR 9814451 A	03-10-2000
		CN 1271371 T	25-10-2000
		CN 1273592 T	15-11-2000
		CN 1275996 T	06-12-2000
		CN 1276811 T	13-12-2000
		EP 1007585 A1	14-06-2000
		EP 1007586 A1	14-06-2000
		EP 1007587 A1	14-06-2000
		EP 1007583 A1	14-06-2000
		EP 1007589 A1	14-06-2000
		EP 1007590 A1	14-06-2000
		HU 0002756 A2	28-12-2000
		NO 20000966 A	25-04-2000
		PL 339083 A1	04-12-2000
		TR 200000516 T2	22-01-2001
		TR 200000905 T2	21-07-2000
		TR 200001175 T2	21-08-2000
		WO 9910421 A1	04-03-1999
		WO 9910422 A1	04-03-1999
		WO 9910423 A1	04-03-1999
		WO 9910415 A1	04-03-1999
		WO 9910426 A1	04-03-1999
		WO 9910427 A1	04-03-1999
		US 6211302 B1	03-04-2001
		US 6143829 A	07-11-2000
US 5929129	A	27-07-1999	
		AU 3600797 A	09-02-1998
		BR 9710310 A	17-08-1999
		CA 2260951 A1	22-01-1998
		EP 0910605 A1	28-04-1999
		JP 2000514856 T	07-11-2000
		WO 9802483 A1	22-01-1998
		EP 0702032 A2	20-03-1996
		JP 8176332 A	09-07-1996
		US 6103775 A	15-08-2000
		US 5932659 A	03-08-1999
		US 5883144 A	16-03-1999
		US 5883145 A	16-03-1999
GB 1022051	A	09-03-1966	
		DE 1544999 A1	27-05-1971